

CDN Resource Laboratories Ltd.

10945-B River Road, Delta, B.C., V4C 2R8, 604 596-2245, Fax: 604 588-3960

ORE REFERENCE STANDARD: CDN-CGS-8

Recommended values and the "Between Lab" Two Standard Deviations

Copper concentration: 0.105 ± 0.008 %
*Gold concentration 0.080 ± 0.012 g/t (provisional value only) ***

PREPARED BY: CDN Resource Laboratories Ltd.
CERTIFIED BY: Duncan Sanderson, B.Sc., Licensed Assayer of British Columbia
INDEPENDENT GEOCHEMIST: Dr. Barry Smee., Ph.D., P. Geo.
DATE OF CERTIFICATION: December 18, 2005

METHOD OF PREPARATION:

Reject ore material was dried, crushed, pulverized and then passed through a 200 mesh screen. The +200 material was discarded. The -200 material was mixed for 5 days in a rotary mixer. After internal assaying to test for homogeneity, splits were taken and sent to 12 laboratories for round robin assaying.

ORIGIN OF REFERENCE MATERIAL:

The ore was supplied by bcMetals Corporation from the Red Chris Property in British Columbia. Most of the mineralization is closely associated with individual and sheeted quartz (\pm carbonate) veining and quartz (\pm carbonate) stockwork zones. It occurs as disseminations and fracture coatings. Pyrite, chalcopyrite and lesser bornite are the principal sulphide minerals. Gold occurs as electrum spatially and genetically associated with the copper mineralization.

Approximate chemical composition is as follows:

	Percent		Percent
SiO ₂	66.6	MgO	1.2
Al ₂ O ₃	13.7	K ₂ O	2.2
Fe ₂ O ₃	5.9	TiO ₂	0.4
CaO	2.6	LOI	2.2
Na ₂ O	3.9		

Statistical Procedures:

The mean and standard deviation for all data was calculated. Outliers were defined as samples beyond the mean ± 2 Standard Deviations from all data. These outliers were removed from the data and a new mean and standard deviation was determined. This method is different from that used by Government agencies in that the actual "between-laboratory" standard deviation is used in the calculations. This produces upper and lower limits that reflect actual individual analyses rather than a grouped set of analyses. The limits can therefore be used to monitor accuracy from individual analyses, unlike the Certified Limits published on other standards.

Results from round-robin assaying are presented on the following page:

Assay Procedures: **Au:** Fire assay pre-concentration, AA or ICP finish (30g sub-sample).
Cu: 4-acid digestion, AA or ICP finish.

STANDARD REFERENCE MATERIAL CDN-CGS-8

	Lab 1	Lab 2	Lab 3	Lab 4	Lab 5	Lab 6	Lab 7	Lab 8	Lab 9	Lab 10	Lab 11	Lab 12
	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t
	0.08	0.083	0.09	0.080	0.087	0.079	0.078	0.09	0.08	0.085	0.07	0.077
	0.09	0.083	0.08	0.087	0.082	0.087	0.070	0.08	0.08	0.090	0.07	0.070
	0.09	0.081	0.08	0.079	0.083	0.081	0.072	0.07	0.07	0.088	0.08	0.075
	0.09	0.074	0.08	0.080	0.077	0.076	0.065	0.07	0.08	0.080	0.08	0.075
	0.08	0.079	0.08	0.076	0.085	0.078	0.070	0.09	0.08	0.086	0.09	0.073
	0.08	0.082	0.08	0.082	0.076	0.081	0.075	0.08	0.07	0.076	0.09	0.070
	0.09	0.080	0.07	0.084	0.075	0.077	0.068	0.08	0.08	0.086	0.09	0.075
	0.08	0.085	0.08	0.080	0.080	0.084	0.064	0.08	0.08	0.073	0.07	0.073
	0.08	0.078	0.10	0.092	0.079	0.081	0.062	0.08	0.08	0.081	0.07	0.080
	0.08	0.086	0.07	0.083	0.082	0.097	0.060	0.08	0.07	0.089	0.07	0.070
Mean	0.084	0.081	0.081	0.082	0.081	0.082	0.068	0.080	0.077	0.083	0.078	0.074
Std Dev	0.005	0.004	0.009	0.005	0.004	0.006	0.006	0.007	0.005	0.006	0.009	0.003
%RSD	6.15	4.37	10.81	5.53	4.87	7.62	8.39	8.33	6.27	6.83	11.78	4.39
	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu
	0.109	0.108	0.115	0.104	0.099	0.109	0.10	0.105	0.10	0.116	0.108	0.106
	0.108	0.108	0.117	0.105	0.097	0.110	0.10	0.103	0.10	0.111	0.108	0.106
	0.109	0.108	0.115	0.102	0.096	0.109	0.10	0.105	0.10	0.113	0.107	0.107
	0.111	0.108	0.116	0.105	0.100	0.109	0.10	0.103	0.10	0.113	0.108	0.105
	0.109	0.106	0.116	0.102	0.099	0.109	0.10	0.105	0.10	0.112	0.108	0.105
	0.108	0.108	0.115	0.101	0.101	0.111	0.10	0.103	0.10	0.112	0.107	0.105
	0.108	0.108	0.116	0.103	0.098	0.109	0.10	0.105	0.10	0.112	0.108	0.105
	0.108	0.108	0.115	0.099	0.098	0.109	0.10	0.105	0.10	0.113	0.108	0.105
	0.110	0.106	0.115	0.100	0.099	0.110	0.10	0.106	0.10	0.112	0.106	0.107
	0.108	0.108	0.115	0.102	0.097	0.110	0.10	0.105	0.10	0.112	0.106	0.106
Mean	0.109	0.108	0.116	0.102	0.098	0.109	0.100	0.105	0.100	0.113	0.107	0.106
Std Dev	0.001	0.001	0.001	0.002	0.002	0.001	0.000	0.001	0.000	0.001	0.001	0.001
%RSD	0.95	0.78	0.61	1.96	1.53	0.54	0.00	1.03	0.00	1.20	0.79	0.74

Note: Au results from Lab. #7 were removed from the data set.
Cu results from Lab. #3 were removed from the data set.

STANDARD REFERENCE MATERIAL CDN-CGS-8

Participating Laboratories:


(not in same order as listed in table of results)

Acme Analytical Laboratories Ltd., Vancouver
Assayers Canada Ltd., Vancouver
ALS Chemex Laboratories, North Vancouver
Alex Stewart Assayers, Argentina
EcoTech Laboratory, Kamloops, B.C.
Genalysis Laboratory Services Pty. Ltd., Australia
GTK Laboratory, (Geological Survey of Finland)
International Plasma Labs. Ltd., Vancouver
OMAC Laboratories Ltd., Ireland
SGS-XRAL, Toronto
Teck Cominco - Global Discovery Laboratory, Vancouver
TSL Laboratories, Saskatoon


Legal Notice:

This certificate and the reference material described in it have been prepared with due care and attention. However CDN Resource Laboratories Ltd. or Barry Smee accept no liability for any decisions or actions taken following the use of the reference material. Our liability is limited solely to the cost of the reference material.

Certified by


Duncan Sanderson, Certified Assayer of B.C.

Geochemist


Dr. Barry Smee, Ph.D., P. Geo.