

# CDN Resource Laboratories Ltd.

#2, 20148 – 102<sup>nd</sup> Ave, Langley, B.C., Canada, V1M 4B4, 604-882-8422, Fax: 604-882-8466 (www.cdnlabs.com)

## REFERENCE MATERIAL: CDN-CM-27

Recommended values and the “Between Lab” Two Standard Deviations

<i>Gold</i>	<i>0.636 g/t ± 0.068 g/t</i>	<i>Certified value</i>	<i>30g FA / ICP or AA</i>
<i>Copper</i>	<i>0.592 % ± 0.030 %</i>	<i>Certified value</i>	<i>4-acid / ICP or AA</i>
<i>Copper</i>	<i>0.593 % ± 0.026 %</i>	<i>Certified value</i>	<i>Aqua regia / ICP or AA</i>
<i>Molybdenum</i>	<i>0.051 % ± 0.004 %</i>	<i>Certified value</i>	<i>4-acid / ICP or AA</i>
<i>Molybdenum</i>	<i>0.051 % ± 0.004 %</i>	<i>Certified value</i>	<i>Aqua regia / ICP or AA</i>

**Note:** Standards with an RSD of near or less than 5% are certified; RSD's of between 5% and 15% are Provisional; RSD's over 15% are Indicated. Provisional and Indicated values cannot be used to monitor accuracy with a high degree of certainty.

**PREPARED BY:** CDN Resource Laboratories Ltd.  
**CERTIFIED BY:** Duncan Sanderson, B.Sc., Licensed Assayer of British Columbia  
**INDEPENDENT GEOCHEMIST:** Dr. Barry Smee., Ph.D., P. Geo.  
**DATE OF CERTIFICATION:** November 2, 2012

### **METHOD OF PREPARATION:**

Reject ore material was dried, crushed, pulverized and then passed through a 270 mesh screen. The +270 material was discarded. The -270 material was mixed for 5 days in a double-cone mixer. Splits were taken and sent to 15 laboratories for round robin assaying.

### **ORIGIN OF REFERENCE MATERIAL:**

Standard CDN-CM-27 was prepared using 800 kg of a granitic rock blended with 22 kg of a Cu-Au-Mo concentrate.

**Approximate chemical composition (from whole rock analysis) is as follows:**

	Percent			Percent
SiO <sub>2</sub>	68.6		MgO	2.0
Al <sub>2</sub> O <sub>3</sub>	11.6		K <sub>2</sub> O	1.1
Fe <sub>2</sub> O <sub>3</sub>	6.6		TiO <sub>2</sub>	0.5
CaO	3.2		LOI	2.0
Na <sub>2</sub> O	2.8		S	0.9
C	0.1			

### **Statistical Procedures:**

The final limits were calculated after first determining if all data was compatible within a spread normally expected for similar analytical methods done by reputable laboratories. Data from any one laboratory was removed from further calculations when the mean of all analyses from that laboratory failed a t test of the global means of the other laboratories. The means and standard deviations were calculated using all remaining data. Any analysis that fell outside of the mean ±2 standard deviations was removed from the ensuing data base. The mean and standard deviations were again calculated using the remaining data. This method is different from that used by Government agencies in that the actual “between-laboratory” standard deviation is used in the calculations. This produces upper and lower limits that reflect actual individual analyses rather than a grouped set of analyses. The limits can therefore be used to monitor accuracy from individual analyses, unlike the Confidence Limits published on other standards.

## REFERENCE MATERIAL CDN-CM-27

### Results from round-robin assaying:

	Lab 1	Lab 2	Lab 3	Lab 4	Lab 5	Lab 6	Lab 7	Lab 8	Lab 9	Lab 10	Lab 11	Lab 12	Lab 13	Lab 14	Lab 15
	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t
CM-27-1	0.620	0.548	0.633	0.674	0.65	0.596	0.59	0.648	0.556	0.633	0.61	0.708	0.658	0.622	0.607
CM-27-2	0.641	0.646	0.648	0.704	0.60	0.635	0.64	0.660	0.575	0.637	0.60	0.675	0.585	0.644	0.600
CM-27-3	0.619	0.632	0.685	0.705	0.69	0.614	0.65	0.679	0.587	0.716	0.61	0.644	0.667	0.649	0.692
CM-27-4	0.608	0.597	0.642	0.669	0.65	0.706	0.63	0.599	0.608	0.694	0.62	0.652	0.664	0.651	0.647
CM-27-5	0.614	0.588	0.631	0.657	0.63	0.669	0.59	0.582	0.544	0.718	0.66	0.695	0.633	0.624	0.671
CM-27-6	0.618	0.629	0.619	0.677	0.64	0.622	0.65	0.582	0.638	0.604	0.60	0.646	0.673	0.633	0.697
CM-27-7	0.678	0.574	0.628	0.650	0.63	0.676	0.61	0.660	0.593	0.665	0.64	0.702	0.583	0.604	0.609
CM-27-8	0.626	0.628	0.614	0.712	0.63	0.612	0.62	0.601	0.597	0.639	0.59	0.662	0.657	0.606	0.629
CM-27-9	0.599	0.608	0.680	0.662	0.62	0.551	0.59	0.579	0.552	0.622	0.59	0.705	0.666	0.637	0.633
CM-27-10	0.600	0.538	0.605	0.684	0.68	0.586	0.69	0.600	0.619	0.619	0.66	0.645	0.677	0.625	0.656
Mean	0.622	0.599	0.639	0.679	0.642	0.627	0.626	0.619	0.587	0.655	0.618	0.673	0.646	0.630	0.644
Std. Devn.	0.0231	0.0368	0.0264	0.0215	0.0270	0.0463	0.0327	0.0383	0.0305	0.0413	0.0266	0.0269	0.0349	0.0164	0.0348
% RSD	3.72	6.15	4.14	3.16	4.21	7.39	5.23	6.19	5.20	6.31	4.30	3.99	5.40	2.61	5.40
4 acid	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu
CM-27-1	0.583	0.568	0.574	0.605	0.588	0.589	0.606	0.563	0.605	0.634	0.592	0.594	0.64	0.596	0.59
CM-27-2	0.571	0.574	0.580	0.605	0.585	0.586	0.602	0.567	0.603	0.643	0.587	0.610	0.65	0.592	0.59
CM-27-3	0.614	0.588	0.618	0.598	0.579	0.600	0.597	0.573	0.606	0.639	0.581	0.610	0.64	0.589	0.59
CM-27-4	0.637	0.568	0.588	0.594	0.590	0.586	0.602	0.559	0.607	0.644	0.596	0.610	0.61	0.602	0.59
CM-27-5	0.587	0.567	0.593	0.599	0.585	0.601	0.601	0.562	0.603	0.625	0.599	0.586	0.60	0.592	0.58
CM-27-6	0.522	0.603	0.618	0.619	0.587	0.579	0.593	0.562	0.598	0.623	0.605	0.581	0.61	0.587	0.59
CM-27-7	0.568	0.563	0.619	0.589	0.582	0.594	0.601	0.559	0.604	0.612	0.599	0.586	0.62	0.595	0.59
CM-27-8	0.575	0.579	0.654	0.598	0.578	0.585	0.598	0.561	0.605	0.585	0.583	0.598	0.61	0.590	0.58
CM-27-9	0.608	0.566	0.604	0.586	0.584	0.575	0.592	0.557	0.603	0.606	0.605	0.596	0.61	0.602	0.59
CM-27-10	0.593	0.558	0.628	0.599	0.582	0.589	0.597	0.565	0.595	0.592	0.593	0.587	0.60	0.594	0.58
Mean	0.586	0.573	0.608	0.599	0.584	0.588	0.599	0.563	0.603	0.620	0.594	0.596	0.619	0.594	0.587
Std. Devn.	0.0311	0.0134	0.0245	0.0092	0.0038	0.0083	0.0044	0.0046	0.0037	0.0210	0.0085	0.0110	0.0179	0.0051	0.0048
% RSD	5.31	2.34	4.04	1.54	0.66	1.41	0.73	0.82	0.61	3.38	1.43	1.84	2.89	0.85	0.82
Aqua regia	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu
CM-27-1	0.605	0.608	0.600	0.596	0.586	0.595	0.606	0.590	0.611	0.569	0.565	0.583	0.59	0.594	0.58
CM-27-2	0.617	0.583	0.602	0.609	0.580	0.609	0.591	0.570	0.606	0.595	0.563	0.586	0.60	0.597	0.58
CM-27-3	0.601	0.602	0.611	0.611	0.577	0.612	0.609	0.575	0.608	0.586	0.572	0.599	0.60	0.578	0.58
CM-27-4	0.601	0.586	0.584	0.592	0.566	0.616	0.598	0.567	0.603	0.591	0.524	0.608	0.61	0.591	0.58
CM-27-5	0.596	0.585	0.597	0.599	0.564	0.606	0.608	0.590	0.605	0.594	0.568	0.585	0.61	0.594	0.58
CM-27-6	0.601	0.576	0.606	0.578	0.585	0.604	0.617	0.578	0.598	0.563	0.568	0.600	0.60	0.576	0.58
CM-27-7	0.591	0.596	0.605	0.584	0.584	0.604	0.612	0.581	0.608	0.590	0.571	0.607	0.61	0.586	0.59
CM-27-8	0.605	0.594	0.601	0.603	0.580	0.600	0.593	0.593	0.603	0.591	0.572	0.600	0.64	0.593	0.58
CM-27-9	0.593	0.600	0.609	0.611	0.566	0.610	0.599	0.583	0.598	0.589	0.570	0.602	0.62	0.603	0.58
CM-27-10	0.593	0.594	0.613	0.600	0.566	0.625	0.589	0.597	0.604	0.589	0.568	0.601	0.63	0.603	0.57
Mean	0.600	0.592	0.603	0.598	0.575	0.608	0.602	0.582	0.604	0.586	0.564	0.597	0.611	0.591	0.580
Std. Devn.	0.0077	0.0098	0.0083	0.0112	0.0089	0.0085	0.0093	0.0100	0.0042	0.0108	0.0142	0.0091	0.0152	0.0093	0.0047
% RSD	1.29	1.65	1.38	1.87	1.55	1.39	1.55	1.73	0.69	1.84	2.53	1.52	2.49	1.58	0.81

**REFERENCE MATERIAL CDN-CM-27**

**Results from round-robin assaying:**

	Lab 1	Lab 2	Lab 3	Lab 4	Lab 5	Lab 6	Lab 7	Lab 8	Lab 9	Lab 10	Lab 11	Lab 12	Lab 13	Lab 14	Lab 15
4 acid	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %
CM-27-1	0.051	0.053	0.049	0.050	0.049	0.050	0.052	0.048	0.051	0.056	0.055	0.049	0.06	0.051	0.05
CM-27-2	0.051	0.055	0.049	0.048	0.049	0.050	0.051	0.049	0.050	0.055	0.053	0.051	0.05	0.052	0.05
CM-27-3	0.052	0.056	0.053	0.050	0.049	0.051	0.050	0.048	0.049	0.055	0.053	0.051	0.05	0.054	0.05
CM-27-4	0.056	0.055	0.050	0.048	0.051	0.051	0.051	0.050	0.050	0.057	0.051	0.052	0.05	0.052	0.05
CM-27-5	0.052	0.057	0.049	0.049	0.050	0.051	0.052	0.050	0.049	0.055	0.054	0.050	0.05	0.054	0.05
CM-27-6	0.046	0.058	0.052	0.052	0.049	0.050	0.050	0.047	0.049	0.055	0.054	0.049	0.06	0.053	0.05
CM-27-7	0.048	0.054	0.052	0.048	0.051	0.050	0.050	0.048	0.050	0.055	0.057	0.049	0.05	0.053	0.05
CM-27-8	0.050	0.054	0.050	0.047	0.050	0.049	0.051	0.048	0.050	0.053	0.056	0.050	0.05	0.051	0.05
CM-27-9	0.052	0.055	0.050	0.048	0.049	0.048	0.051	0.048	0.056	0.055	0.054	0.049	0.05	0.053	0.05
CM-27-10	0.052	0.053	0.051	0.049	0.051	0.048	0.051	0.049	0.048	0.053	0.050	0.049	0.06	0.051	0.05
Mean	0.051	0.055	0.051	0.049	0.050	0.050	0.051	0.048	0.050	0.055	0.054	0.050	0.053	0.052	0.050
Std. Devn.	0.0027	0.0016	0.0016	0.0015	0.0008	0.0011	0.0008	0.0008	0.0021	0.0012	0.0021	0.0010	0.0048	0.0014	0.0000
% RSD	5.23	2.97	3.11	3.10	1.68	2.19	1.66	1.67	4.29	2.18	3.83	2.03	9.11	2.65	0.00
Aqua regia	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %
CM-27-1	0.053	0.054	0.052	0.045	0.050	0.039	0.051	0.053	0.051	0.051	0.037	0.050	0.06	0.051	0.05
CM-27-2	0.055	0.053	0.053	0.048	0.049	0.040	0.050	0.052	0.052	0.054	0.038	0.050	0.06	0.051	0.05
CM-27-3	0.053	0.055	0.053	0.048	0.048	0.042	0.051	0.052	0.052	0.052	0.038	0.051	0.06	0.051	0.05
CM-27-4	0.053	0.054	0.051	0.047	0.048	0.041	0.050	0.053	0.051	0.053	0.037	0.051	0.06	0.051	0.04
CM-27-5	0.053	0.054	0.052	0.044	0.048	0.043	0.052	0.053	0.053	0.052	0.036	0.049	0.06	0.051	0.05
CM-27-6	0.053	0.055	0.053	0.045	0.049	0.041	0.053	0.053	0.051	0.050	0.038	0.051	0.06	0.050	0.04
CM-27-7	0.052	0.055	0.052	0.045	0.050	0.037	0.053	0.054	0.053	0.053	0.037	0.051	0.06	0.050	0.05
CM-27-8	0.054	0.055	0.052	0.046	0.050	0.035	0.051	0.052	0.050	0.053	0.038	0.051	0.05	0.052	0.04
CM-27-9	0.053	0.054	0.053	0.046	0.050	0.036	0.051	0.054	0.050	0.053	0.037	0.051	0.06	0.051	0.05
CM-27-10	0.052	0.054	0.054	0.046	0.050	0.037	0.050	0.054	0.051	0.052	0.038	0.051	0.06	0.052	0.05
Mean	0.053	0.054	0.053	0.046	0.049	0.039	0.051	0.053	0.051	0.052	0.037	0.051	0.059	0.051	0.047
Std. Devn.	0.0009	0.0007	0.0007	0.0013	0.0010	0.0028	0.0010	0.0006	0.0008	0.0012	0.0006	0.0009	0.0032	0.0006	0.0048
% RSD	1.65	1.24	1.40	2.85	2.09	7.21	1.93	1.18	1.64	2.22	1.64	1.71	5.36	1.18	10.28

**Note:** Aqua regia Mo results from Labs 6 and 11 were removed for failing the t test.

**REFERENCE MATERIAL CDN-CM-27**

**Participating Laboratories:**


(not in same order as listed in table of results)

Acme Analytical Laboratories Ltd., Vancouver, B.C., Canada  
Acme Analytical Laboratories Ltd., Santiago, Chile  
Actlabs, Ancaster, Ontario, Canada  
Actlabs, Thunder Bay, Ontario, Canada  
ALS Chemex Laboratories, North Vancouver, B.C., Canada  
AGAT, Mississauga, Ontario, Canada  
Alex Stewart, Mendoza, Argentina  
Certimin, Lima, Peru  
Inspectorate Exploration & Mining Services, Richmond, B.C., Canada  
Intertek - Genalysis, Perth, Australia  
SGS, Lima, Peru  
SGS, Toronto, Ontario, Canada  
SGS, Vancouver, B.C., Canada  
TSL Laboratories, Saskatoon, Canada  
Ultra Trace (Bureau Veritas), Perth, Australia


**Legal Notice:**

This certificate and the reference material described in it have been prepared with due care and attention. However CDN Resource Laboratories Ltd. or Barry Smee accept no liability for any decisions or actions taken following the use of the reference material. Our liability is limited solely to the cost of the reference material.

Certified by

  
Duncan Sanderson, Certified Assayer of B.C.

Geochemist

  
Dr. Barry Smee, Ph.D., P. Geo.