

# CDN Resource Laboratories Ltd.

#2, 20148 – 102<sup>nd</sup> Avenue, Langley, B.C., Canada, V1M 4B4, 604-882-8422, Fax: 604-882-8466 (www.cdnlabs.com)

## ORE REFERENCE STANDARD: CDN-CM-5

Recommended values and the “Between Lab” Two Standard Deviations

*Gold:*                 $0.294 \pm 0.046$  g/t  
*Copper:*             $0.319 \pm 0.020$  %  
*Molybdenum:*     $0.050 \pm 0.005$  %

**PREPARED BY:**        CDN Resource Laboratories Ltd.  
**CERTIFIED BY:**        Duncan Sanderson, B.Sc., Licensed Assayer of British Columbia  
**INDEPENDENT GEOCHEMIST:** Dr. Barry Smee., Ph.D., P. Geo.  
**DATE OF CERTIFICATION:** January 18, 2008

### **METHOD OF PREPARATION:**

Reject ore material was dried, crushed, pulverized and then passed through a 200 mesh screen. The +200 material was discarded. The -200 material was mixed for 7 days in a double-cone blender. Splits were taken and sent to 12 laboratories for round robin assaying.

### **ORIGIN OF REFERENCE MATERIAL:**

Standard CDN-CM-5 was prepared using ore supplied by Canadian Gold Hunter from their GJ property in British Columbia, Canada. It is a copper-gold porphyry deposit and the rocks are described as Upper Triassic, quartz deficient volcanics, sediments and coeval intrusive. The standard was prepared using 760 kg of this ore and 11 kg of a high-grade molybdenum ore.

### **Approximate chemical composition is as follows:**

	Percent			Percent
SiO <sub>2</sub>	53.5		MgO	2.6
Al <sub>2</sub> O <sub>3</sub>	14.7		K <sub>2</sub> O	2.7
Fe <sub>2</sub> O <sub>3</sub>	7.7		TiO <sub>2</sub>	0.6
CaO	6.6		LOI	7.2
Na <sub>2</sub> O	2.6		S	1.8

### **Statistical Procedures:**

The final limits were calculated after first determining if all data was compatible within a spread normally expected for similar analytical methods done by reputable laboratories. Data from any one laboratory was removed from further calculations when the mean of all analyses from that laboratory failed a t test of the global means of the other laboratories. The means and standard deviations were calculated using all remaining data. Any analysis that fell outside of the mean  $\pm 2$  standard deviations was removed from the ensuing data base. The mean and standard deviations were again calculated using the remaining data. This method is different from that used by Government agencies in that the actual “between-laboratory” standard deviation is used in the calculations. This produces upper and lower limits that reflect actual individual analyses rather than a grouped set of analyses. The limits can therefore be used to monitor accuracy from individual analyses, unlike the Confidence Limits published on other standards.

**Results from round-robin assaying are displayed on the following page.**

## STANDARD REFERENCE MATERIAL CDN-CM-5

**Assay Procedures:**    **Au:**    Fire assay pre-concentration, AA or ICP finish (30g sub-sample).

**Cu, Mo:**    4-acid digestion, AA or ICP finish.

	Lab 1	Lab 2	Lab 3	Lab 4	Lab 5	Lab 6	Lab 7	Lab 8	Lab 9	Lab 10	Lab 11	Lab 12
SAMPLE	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t
CM5-1	0.285	0.332	0.303	0.286	0.30	0.250	0.300	0.240	0.280	0.288	0.275	0.324
CM5-2	0.324	0.303	0.286	0.292	0.27	0.280	0.300	0.282	0.280	0.264	0.274	0.301
CM5-3	0.297	0.315	0.345	0.302	0.25	0.260	0.310	0.285	0.280	0.328	0.329	0.271
CM5-4	0.275	0.350	0.307	0.303	0.28	0.330	0.290	0.312	0.310	0.324	0.285	0.326
CM5-5	0.290	0.314	0.262	0.313	0.26	0.290	0.290	0.290	0.290	0.284	0.275	0.329
CM5-6	0.269	0.299	0.298	0.306	0.28	0.300	0.330	0.289	0.330	0.292	0.303	0.331
CM5-7	0.267	0.308	0.308	0.317	0.30	0.300	0.300	0.302	0.280	0.274	0.306	0.364
CM5-8	0.345	0.396	0.346	0.289	0.27	0.360	0.300	0.294	0.290	0.254	0.306	0.285
CM5-9	0.284	0.305	0.292	0.258	0.34	0.270	0.350	0.274	0.300	0.248	0.273	0.279
CM5-10	0.285	0.308	0.294	0.267	0.27	0.260	0.330	0.253	0.290	0.254	0.315	0.278
Mean	0.292	0.323	0.304	0.293	0.282	0.290	0.310	0.282	0.293	0.281	0.294	0.309
Std. Dev'n	0.0246	0.0299	0.0255	0.0191	0.0257	0.0343	0.0200	0.0217	0.0164	0.0281	0.0202	0.0305
%RSD	8.44	9.25	8.38	6.52	9.13	11.83	6.45	7.69	5.58	10.01	6.87	9.87
	Cu %	Cu %	Cu %	Cu %	Cu %	Cu %	Cu %	Cu %	Cu %	Cu %	Cu %	Cu %
CM5-1	0.332	0.306	0.327	0.348	0.323	0.334	0.310	0.323	0.306	0.321	0.319	0.328
CM5-2	0.325	0.303	0.316	0.343	0.325	0.336	0.309	0.327	0.308	0.331	0.318	0.330
CM5-3	0.338	0.307	0.323	0.341	0.322	0.333	0.309	0.325	0.305	0.327	0.306	0.333
CM5-4	0.347	0.304	0.321	0.339	0.303	0.343	0.308	0.327	0.307	0.320	0.320	0.324
CM5-5	0.328	0.303	0.321	0.349	0.315	0.345	0.308	0.323	0.306	0.319	0.312	0.300
CM5-6	0.332	0.304	0.317	0.344	0.318	0.336	0.307	0.326	0.310	0.321	0.322	0.326
CM5-7	0.327	0.308	0.321	0.342	0.315	0.339	0.309	0.330	0.305	0.323	0.324	0.330
CM5-8	0.329	0.304	0.313	0.348	0.312	0.340	0.308	0.330	0.309	0.330	0.307	0.324
CM5-9	0.336	0.307	0.325	0.347	0.313	0.344	0.309	0.327	0.309	0.313	0.328	0.323
CM5-10	0.323	0.304	0.325	0.340	0.310	0.342	0.309	0.328	0.307	0.318	0.320	0.315
Mean	0.332	0.305	0.321	0.344	0.316	0.339	0.309	0.326	0.307	0.322	0.318	0.323
Std. Dev'n	0.0071	0.0018	0.0044	0.0037	0.0067	0.0045	0.0008	0.0025	0.0018	0.0056	0.007	0.0096
%RSD	2.15	0.60	1.38	1.07	2.11	1.32	0.27	0.76	0.57	1.74	2.25	2.96
	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %	Mo %
CM5-1	0.050	0.043		0.049	0.048	0.054	0.050	0.052	0.048	0.047	0.055	0.053
CM5-2	0.049	0.042		0.049	0.048	0.055	0.049	0.053	0.050	0.049	0.050	0.055
CM5-3	0.051	0.043		0.047	0.048	0.053	0.049	0.053	0.049	0.048	0.048	0.055
CM5-4	0.052	0.041		0.050	0.047	0.055	0.049	0.053	0.050	0.048	0.056	0.054
CM5-5	0.049	0.045		0.048	0.047	0.056	0.049	0.053	0.050	0.047	0.047	0.049
CM5-6	0.051	0.045		0.047	0.047	0.055	0.048	0.053	0.050	0.046	0.049	0.054
CM5-7	0.050	0.044		0.048	0.048	0.055	0.048	0.053	0.050	0.048	0.055	0.051
CM5-8	0.049	0.042		0.049	0.047	0.055	0.049	0.054	0.050	0.047	0.049	0.053
CM5-9	0.051	0.042		0.049	0.048	0.057	0.049	0.053	0.049	0.047	0.050	0.055
CM5-10	0.049	0.045		0.046	0.046	0.055	0.049	0.054	0.049	0.048	0.050	0.052
Mean	0.050	0.043		0.048	0.047	0.055	0.049	0.053	0.050	0.048	0.051	0.053
Std. Dev'n	0.0011	0.0015		0.0012	0.0007	0.0009	0.0006	0.0005	0.0007	0.0008	0.0032	0.0020
%RSD	2.24	3.42		2.55	1.48	1.62	1.16	0.90	1.43	1.79	6.35	3.71

**Note:**    *“Cu” data from laboratory 4 was excluded from the calculations for failing the t test.*  
                  *“Mo” data from laboratory 2 was excluded from the calculations for failing the t test.*  
                  *Laboratory 3 did not report for “Mo” data.*

**STANDARD REFERENCE MATERIAL CDN-CM-5**

**Participating Laboratories:**


(not in same order as listed in table of results)

Acme Analytical Laboratories Ltd., Vancouver B.C.  
Activation Laboratories Ltd., Ontario  
Assayers Canada Ltd., Vancouver B.C.  
ALS Chemex Laboratories, North Vancouver  
Alex Stewart Assayers, Argentina  
Genalysis Laboratory Services Pty. Ltd., Australia  
American Assay Labs, USA  
Labtium, Finland  
OMAC Laboratories Ltd., Ireland  
Skyline Assayers & Laboratories, Tucson, USA  
TSL Laboratories, Saskatoon  
Ultra Trace Analytical Laboratories, Australia

Legal Notice:

This certificate and the reference material described in it have been prepared with due care and attention. However CDN Resource Laboratories Ltd. or Barry Smee accept no liability for any decisions or actions taken following the use of the reference material. Our liability is limited solely to the cost of the reference material.

Certified by



Duncan Sanderson, Certified Assayer of B.C.

Geochemist



Dr. Barry Smee, Ph.D., P. Geo.