

CDN Resource Laboratories Ltd.

#2, 20148 – 102nd Avenue, Langley, B.C., Canada, V1M 4B4, 604-882-8422, Fax: 604-882-8466 (www.cdnlabs.com)

REFERENCE MATERIAL: CDN-GS-6C

Recommended value and the "Between Laboratory" two standard deviations

Gold concentration: 6.03 ± 0.56 g/t (30g Fire Assay / instrumental finish)

Gold concentration: 5.95 ± 0.48 g/t (30g Fire Assay / gravimetric finish)

PREPARED BY: CDN Resource Laboratories Ltd.

CERTIFIED BY: Duncan Sanderson, B.Sc., Licensed Assayer of British Columbia

INDEPENDENT GEOCHEMIST: Dr. Barry Smee., Ph.D., P. Geo.

DATE OF CERTIFICATION: October 21, 2011

ORIGIN OF REFERENCE MATERIAL:

Standard CDN-GS-6C was prepared using a combination of several different siliceous ores with low sulphidation.

METHOD OF PREPARATION:

Reject ore material was dried, crushed, pulverized and then passed through a 270 mesh screen. The +270 material was discarded. The -270 material was mixed for 5 days in a double-cone blender. Splits were taken and sent to 15 commercial laboratories for round robin assaying. Round robin results are displayed below:

	Lab 1 Au g/t	Lab 2 Au g/t	Lab 3 Au g/t	Lab 4 Au g/t	Lab 5 Au g/t	Lab 6 Au g/t	Lab 7 Au g/t	Lab 8 Au g/t	Lab 9 Au g/t	Lab 10 Au g/t	Lab 11 Au g/t	Lab 12 Au g/t	Lab 13 Au g/t	Lab 14 Au g/t	Lab 15 Au g/t
GS-6C-1	5.77	6.47	6.38	5.88	5.91	5.88	6.13	6.18	5.88		5.53	6.05	6.29	5.88	5.89
GS-6C-2	6.19	6.12	6.50	5.80	6.07	5.72	6.36	5.77	5.54		5.56	6.25	6.10	5.63	6.07
GS-6C-3	6.09	6.35	6.44	6.07	5.91	5.74	6.40	5.83	5.81		5.53	6.13	6.22	5.79	6.51
GS-6C-4	5.62	6.68	6.65	6.06	5.60	5.58	6.19	7.24	5.27		5.71	6.28	6.26	6.00	6.27
GS-6C-5	5.96	6.17	6.42	5.80	6.59	5.76	6.40	6.09	5.52		5.66	6.37	6.34	5.77	6.01
GS-6C-6	6.11	6.24	6.48	5.95	5.90	5.89	6.13	5.94	5.36		5.60	6.27	6.33	5.57	5.87
GS-6C-7	5.99	6.09	6.50	6.08	6.04	5.77	6.45	5.65	5.28		5.86	6.29	6.41	5.93	6.37
GS-6C-8	5.80	6.65	6.54	5.96	5.94	5.92	6.64	5.79	4.92		5.49	6.29	6.16	5.83	6.34
GS-6C-9	5.57	6.37	6.20	6.10	5.85	5.89	6.22	6.10	5.21		5.50	5.84	6.35	5.79	5.80
GS-6C-10	5.88	6.34	6.35	5.94	5.81	5.60	6.12	5.96	5.39		5.72	5.80	6.57	5.70	5.95
Mean	5.90	6.35	6.45	5.96	5.96	5.78	6.30	6.05	5.42		5.62	6.16	6.30	5.79	6.11
Std. Dev'n	0.2083	0.2053	0.1212	0.1114	0.2566	0.1209	0.1725	0.4477	0.2831		0.1184	0.1993	0.1323	0.1312	0.2453
%RSD	3.53	3.23	1.88	1.87	4.31	2.09	2.74	7.40	5.23		2.11	3.24	2.10	2.27	4.02
Gravimetric	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t									
GS-6C-1	6.07	6.30	6.40	6.11	6.10	5.81	5.89		6.00	5.84	5.27	5.99	5.96	5.93	5.53
GS-6C-2	5.95	6.23	6.63	5.86	5.70	5.48	6.14		5.86	5.90	5.93	6.29	6.05	5.90	5.78
GS-6C-3	6.04	6.10	6.33	6.03	6.20	5.86	5.76		5.86	5.87	5.67	6.31	5.73	5.57	6.38
GS-6C-4	5.99	6.47	6.20	5.93	5.70	5.84	6.03		5.79	5.85	5.73	5.95	5.84	6.03	6.16
GS-6C-5	6.04	6.20	6.53	5.82	5.90	5.59	5.81		6.07	5.91	5.27	6.47	6.01	5.97	5.86
GS-6C-6	5.99	6.30	6.43	6.04	5.80	5.77	5.83		5.49	5.94	5.40	6.18	5.99	6.00	6.14
GS-6C-7	5.95	6.13	6.27	6.00	6.00	5.42	6.01		5.52	5.83	5.93	6.38	5.91	6.30	5.88
GS-6C-8	6.02	6.60	6.40	6.15	6.00	5.44	6.15		5.76	5.85	5.27	6.09	5.74	5.83	5.39
GS-6C-9	5.99	6.20	6.33	5.92	5.80	5.50	6.03		6.10	5.95	5.80	6.14	6.06	5.90	5.68
GS-6C-10	5.90	6.43	6.53	5.79	6.10	5.79	5.98		5.62	5.98	5.73	6.24	5.83	5.80	5.41
Mean	5.99	6.30	6.41	5.96	5.93	5.65	5.96		5.81	5.89	5.60	6.20	5.91	5.92	5.82
Std. Dev'n	0.0510	0.1590	0.1308	0.1209	0.1767	0.1801	0.1356		0.2156	0.0520	0.2737	0.1665	0.1218	0.1860	0.3324
%RSD	0.85	2.53	2.04	2.03	2.98	3.19	2.27		3.71	0.88	4.89	2.68	2.06	3.14	5.71

Some laboratories did not report results by both gravimetric and AA / ICP finishes.

Note: Instrumental Au data from Lab 9 was excluded for failing the t test.

REFERENCE MATERIAL: CDN-GS-6C

APPROXIMATE CHEMICAL COMPOSITION (by whole rock analysis):

	Percent		Percent		ppm	
SiO ₂	64.2		Na ₂ O	1.6	As	65
Al ₂ O ₃	10.5		MgO	3.2	Sb	10
Fe ₂ O ₃	10.0		K ₂ O	1.7		
CaO	2.0		TiO ₂	0.3		
MnO	0.1		LOI	5.7		
Total S	4.0		Total C	0.6		

Statistical Procedures:

The final limits were calculated after first determining if all data was compatible within a spread normally expected for similar analytical methods done by reputable laboratories. Data from any one laboratory was removed from further calculations when the mean of all analyses from that laboratory failed a t test of the global means of the other laboratories. The mean and standard deviation were calculated using all remaining data. Any analysis that fell outside of the mean ± 2 standard deviations was removed from the ensuing data base. The mean and standard deviations were again calculated using the remaining data. This method is different from that used by Government agencies in that the actual "between-laboratory" standard deviation is used in the calculations. This produces upper and lower limits that reflect actual individual analyses rather than a grouped set of analyses. The limits can therefore be used to monitor accuracy from individual analyses, unlike the Confidence Limits published on other standards.

Participating Laboratories: (not in same order as table of assays)

Acme Analytical Laboratories Ltd., Vancouver, B.C., Canada
 Activation Laboratories, Ancaster, Ontario, Canada
 Activation Laboratories, Thunder Bay, Ontario, Canada
 AGAT, Mississauga, Ontario
 ALS Chemex, North Vancouver, B.C., Canada
 American Assay Laboratories, Nevada, USA
 CIMM, Lima, Peru
 Inspectorate America Corporation, Richmond, B.C., Canada
 Labtium Inc., Finland
 OMAC Laboratories Ltd., Ireland
 Skyline, Arizona, USA
 SGS, Lima, Peru
 Stewart Group., Kamloops, B.C., Canada
 Alex Stewart Argentina SA
 TSL Laboratories Ltd., Saskatoon, SK, Canada

Legal Notice:

This certificate and the reference material described in it have been prepared with due care and attention. However CDN Resource Laboratories Ltd. nor Barry Smee accept any liability for any decisions or actions taken following the use of the reference material. Our liability is limited solely to the cost of the reference material.

Certified by

Duncan Sanderson

 Duncan Sanderson, Certified Assayer of B.C.

Geochemist

Barry Smee

 Dr. Barry Smee, Ph.D., P. Geo.