

CDN Resource Laboratories Ltd.

#2, 20148 – 102nd Ave, Langley, B.C., Canada, V1M 4B4, 604-882-8422, Fax: 604-882-8466 (www.cdnlabs.com)

REFERENCE MATERIAL: CDN-ME-1311

Recommended values and the “Between Lab” Two Standard Deviations

<i>Gold</i>	<i>0.839 g/t ± 0.066 g/t</i>	<i>Certified value</i>
<i>Silver</i>	<i>44.9 g/t ± 2.2 g/t</i>	<i>Certified value</i>
<i>Copper</i>	<i>0.468 % ± 0.022 %</i>	<i>Certified value</i>
<i>Lead</i>	<i>0.303 % ± 0.012 %</i>	<i>Certified value</i>
<i>Zinc</i>	<i>1.12 % ± 0.04 %</i>	<i>Certified value</i>

Note: Standards with an RSD of near or less than 5% are certified; RSD's of between 5% and 15% are Provisional; RSD's over 15% are Indicated. Provisional and Indicated values cannot be used to monitor accuracy with a high degree of certainty.

PREPARED BY: CDN Resource Laboratories Ltd.
CERTIFIED BY: Duncan Sanderson, B.Sc., Licensed Assayer of British Columbia
INDEPENDENT GEOCHEMIST: Dr. Barry Smee., Ph.D., P. Geo.
DATE OF CERTIFICATION: March 20, 2014

METHOD OF PREPARATION:

Reject ore material was dried, crushed, pulverized and then passed through a 270 mesh screen. The +270 material was discarded. The -270 material was mixed for 5 days in a double-cone mixer. Splits were taken and sent to 15 laboratories for round robin assaying.

ORIGIN OF REFERENCE MATERIAL:

The ore was supplied by Farallon Resources from their Campo Morado property in Mexico. The Campo Morado precious-metal-bearing, volcanogenic massive sulphide deposits occur in a lower Cretaceous bimodal, calc-alkaline volcanic sequence. Most deposits occur in the upper part of a sequence of felsic flows and heterolithic volcanoclastic rocks or at its contact with overlying chert and argillite. Gold, silver, zinc, and lead are associated with pyrite, quartz, ankerite, sphalerite, chalcopyrite and galena, with minor tennantite-freibergite, arsenopyrite, and pyrrhotite.

Approximate chemical composition (from whole rock analysis) is as follows:

	Percent		Percent
SiO ₂	36.2	MgO	2.0
Al ₂ O ₃	4.8	K ₂ O	0.7
Fe ₂ O ₃	28.4	TiO ₂	0.2
CaO	2.6	LOI	22.4
Na ₂ O	0.1	S	17.5
C	1.3		

Statistical Procedures:

The final limits were calculated after first determining if all data was compatible within a spread normally expected for similar analytical methods done by reputable laboratories. Data from any one laboratory was removed from further calculations when the mean of all analyses from that laboratory failed a t test of the global means of the other laboratories. The means and standard deviations were calculated using all remaining data. Any analysis that fell outside of the mean ± 2 standard deviations was removed from the ensuing data base. The mean and standard deviations were again calculated using the remaining data. This method is different from that used by Government agencies in that the actual “between-laboratory” standard deviation is used in the calculations. This produces upper and lower limits that reflect actual individual analyses rather than a grouped set of analyses. The limits can therefore be used to monitor accuracy from individual analyses, unlike the Confidence Limits published on other standards.

Assay Procedures:

Au: Fire assay pre-concentration, AA or ICP finish.
Ag, Cu, Pb, Zn: 4-acid digestion, AA or ICP finish.

REFERENCE MATERIAL CDN-ME-1311

Results from round-robin assaying:

	Lab 1	Lab 2	Lab 3	Lab 4	Lab 5	Lab 6	Lab 7	Lab 8	Lab 9	Lab 10	Lab 11	Lab 12	Lab 13	Lab 14	Lab 15
	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t
ME-1311-1	0.777	0.806	0.855	0.814	0.813	0.824	0.871	0.90	0.800	0.86	0.810	0.865	0.833	0.806	0.66
ME-1311-2	0.784	0.881	0.998	0.816	0.790	0.869	0.803	0.85	0.805	0.79	0.818	0.827	0.892	0.818	0.73
ME-1311-3	0.774	0.831	0.916	0.825	0.819	0.874	0.864	0.91	0.812	0.84	0.821	0.829	0.904	0.829	0.71
ME-1311-4	0.860	0.810	0.879	0.877	0.794	0.832	0.829	0.88	0.808	0.85	0.829	0.802	0.828	0.831	0.66
ME-1311-5	0.811	0.832	0.912	0.848	0.852	0.848	0.804	0.88	0.802	0.86	0.796	0.840	0.905	0.838	0.66
ME-1311-6	0.833	0.872	0.892	0.810	0.827	0.859	0.796	0.91	0.790	0.81	0.874	0.834	0.862	0.826	0.69
ME-1311-7	0.830	0.852	0.838	0.814	0.856	0.853	0.842	0.90	0.808	0.81	0.805	0.814	0.897	0.831	0.68
ME-1311-8	0.829	0.851	0.896	0.853	0.815	0.839	0.831	0.91	0.810	0.87	0.799	0.835	0.869	0.831	0.65
ME-1311-9	0.827	0.822	0.958	0.800	0.897	0.845	0.812	0.87	0.816	0.87	0.802	0.802	0.932	0.850	0.66
ME-1311-10	0.831	0.828	0.902	0.854	0.863	0.874	0.838	0.90	0.783	0.83	0.799	0.867	0.919	0.857	0.71
Mean	0.816	0.839	0.905	0.831	0.833	0.852	0.829	0.891	0.803	0.839	0.815	0.832	0.884	0.832	0.681
Std. Devn.	0.0284	0.0250	0.0466	0.0251	0.0337	0.0174	0.0257	0.0202	0.0102	0.0281	0.0233	0.0225	0.0350	0.0145	0.0277
% RSD	3.48	2.98	5.15	3.02	4.05	2.04	3.09	2.27	1.27	3.35	2.86	2.70	3.96	1.75	4.06
	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t
ME-1311-1	45	44	45	45	44	47	45.0	46	45	44	40	46	44	44.4	44
ME-1311-2	45	44	46	45	43	46	44.5	46	46	44	40	46	44	43.2	44
ME-1311-3	46	43	44	47	44	46	44.7	46	46	44	40	45	45	43.8	44
ME-1311-4	47	44	46	46	43	47	44.4	44	46	43	42	46	44	44.5	44
ME-1311-5	46	44	45	46	45	46	43.7	46	45	44	40	46	46	43.9	43
ME-1311-6	47	46	46	47	44	46	44.6	46	45	45	38	46	45	43.5	42
ME-1311-7	45	44	47	46	45	46	47.3	46	46	43	41	46	45	44.4	43
ME-1311-8	45	44	45	47	44	44	44.1	45	45	43	43	46	45	43.6	42
ME-1311-9	45	44	45	47	45	45	45.0	46	46	44	36	46	45	43.9	42
ME-1311-10	45	45	45	48	44	45	45.0	46	45	43	39	46	44	43.7	43
Mean	45.6	44.2	45.4	46.4	44.1	45.8	44.8	45.7	45.5	43.7	40.0	45.9	44.7	43.9	42.9
Std. Devn.	0.8433	0.7888	0.8433	0.9661	0.7379	0.9189	0.9638	0.5446	0.5270	0.6749	2.0019	0.3162	0.6749	0.4280	0.7379
% RSD	1.85	1.78	1.86	2.08	1.67	2.01	2.15	1.19	1.16	1.54	5.00	0.69	1.51	0.98	1.72

Notes: Au data from laboratory 15 was removed for failing the t test.
Ag data from laboratory 11 was removed for failing the t test.

REFERENCE MATERIAL CDN-ME-1311

Results from round-robin assaying:

	Lab 1	Lab 2	Lab 3	Lab 4	Lab 5	Lab 6	Lab 7	Lab 8	Lab 9	Lab 10	Lab 11	Lab 12	Lab 13	Lab 14	Lab 15
	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu
ME-1311-1	0.453	0.464	0.458	0.455	0.463	0.467	0.470	0.462	0.47	0.474	0.45	0.48	0.450	0.466	0.487
ME-1311-2	0.446	0.463	0.465	0.469	0.457	0.469	0.453	0.466	0.47	0.471	0.44	0.49	0.456	0.468	0.486
ME-1311-3	0.457	0.456	0.447	0.472	0.464	0.475	0.470	0.467	0.47	0.475	0.45	0.49	0.460	0.463	0.479
ME-1311-4	0.464	0.474	0.468	0.468	0.454	0.484	0.483	0.465	0.47	0.476	0.44	0.48	0.451	0.465	0.478
ME-1311-5	0.467	0.475	0.454	0.476	0.454	0.476	0.533	0.458	0.46	0.471	0.45	0.49	0.458	0.471	0.482
ME-1311-6	0.466	0.477	0.470	0.487	0.457	0.473	0.494	0.463	0.47	0.470	0.45	0.49	0.459	0.466	0.475
ME-1311-7	0.455	0.469	0.471	0.479	0.464	0.482	0.515	0.463	0.46	0.476	0.45	0.49	0.457	0.477	0.491
ME-1311-8	0.456	0.467	0.464	0.480	0.466	0.472	0.492	0.465	0.46	0.471	0.45	0.49	0.456	0.467	0.485
ME-1311-9	0.462	0.474	0.454	0.468	0.470	0.467	0.484	0.466	0.46	0.469	0.41	0.49	0.456	0.468	0.475
ME-1311-10	0.455	0.468	0.471	0.479	0.464	0.492	0.518	0.460	0.46	0.483	0.44	0.49	0.456	0.482	0.476
Mean	0.458	0.469	0.462	0.473	0.461	0.476	0.491	0.463	0.465	0.474	0.443	0.488	0.456	0.469	0.481
Std. Devn.	0.0066	0.0065	0.0085	0.0089	0.0054	0.0081	0.0248	0.0029	0.0053	0.0041	0.0125	0.0042	0.0032	0.0060	0.0056
% RSD	1.43	1.39	1.83	1.88	1.18	1.71	5.04	0.62	1.13	0.87	2.83	0.86	0.70	1.28	1.17
	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb
ME-1311-1	0.29	0.301	0.298	0.300	0.298	0.312	0.310	0.306	0.31	0.317	0.28	0.30	0.256	0.301	0.298
ME-1311-2	0.29	0.304	0.300	0.299	0.293	0.312	0.294	0.306	0.30	0.319	0.30	0.30	0.267	0.300	0.308
ME-1311-3	0.30	0.299	0.303	0.312	0.295	0.309	0.304	0.309	0.31	0.316	0.30	0.30	0.262	0.302	0.303
ME-1311-4	0.30	0.310	0.308	0.303	0.290	0.320	0.304	0.305	0.31	0.317	0.30	0.30	0.258	0.303	0.298
ME-1311-5	0.30	0.307	0.300	0.308	0.297	0.313	0.303	0.302	0.31	0.316	0.29	0.30	0.262	0.301	0.308
ME-1311-6	0.30	0.312	0.298	0.313	0.297	0.310	0.302	0.304	0.31	0.314	0.28	0.30	0.266	0.302	0.294
ME-1311-7	0.29	0.307	0.303	0.310	0.301	0.307	0.309	0.305	0.30	0.319	0.30	0.31	0.259	0.306	0.306
ME-1311-8	0.30	0.304	0.296	0.312	0.299	0.303	0.303	0.302	0.31	0.312	0.30	0.30	0.258	0.300	0.299
ME-1311-9	0.30	0.310	0.300	0.308	0.301	0.306	0.304	0.303	0.31	0.312	0.26	0.30	0.263	0.303	0.294
ME-1311-10	0.29	0.309	0.311	0.313	0.294	0.301	0.313	0.305	0.30	0.310	0.29	0.30	0.260	0.303	0.305
Mean	0.296	0.306	0.302	0.308	0.297	0.309	0.305	0.305	0.307	0.315	0.290	0.301	0.261	0.302	0.301
Std. Devn.	0.0052	0.0042	0.0047	0.0053	0.0035	0.0055	0.0052	0.0024	0.0048	0.0033	0.0133	0.0032	0.0036	0.0016	0.0054
% RSD	1.74	1.38	1.56	1.73	1.19	1.76	1.71	0.78	1.57	1.03	4.60	1.05	1.37	0.54	1.79
	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn
ME-1311-1	1.06	1.09	1.14	1.11	1.10	1.11	1.12	1.12	1.11	1.15	1.14	1.10	1.04	1.11	1.12
ME-1311-2	1.05	1.09	1.15	1.14	1.09	1.12	1.13	1.14	1.09	1.15	1.13	1.10	1.05	1.11	1.13
ME-1311-3	1.08	1.08	1.11	1.16	1.10	1.13	1.13	1.13	1.10	1.13	1.13	1.11	1.08	1.12	1.11
ME-1311-4	1.09	1.12	1.15	1.15	1.09	1.15	1.12	1.13	1.10	1.14	1.13	1.09	1.14	1.11	1.14
ME-1311-5	1.10	1.11	1.14	1.17	1.09	1.13	1.16	1.13	1.09	1.15	1.15	1.10	1.09	1.11	1.12
ME-1311-6	1.10	1.13	1.15	1.19	1.08	1.12	1.11	1.13	1.10	1.12	1.13	1.10	1.04	1.11	1.10
ME-1311-7	1.08	1.11	1.16	1.17	1.09	1.14	1.11	1.11	1.10	1.14	1.14	1.11	1.16	1.12	1.13
ME-1311-8	1.07	1.10	1.14	1.18	1.11	1.11	1.13	1.11	1.10	1.13	1.15	1.12	1.19	1.10	1.12
ME-1311-9	1.09	1.13	1.11	1.15	1.13	1.11	1.10	1.12	1.09	1.12	1.04	1.11	1.13	1.11	1.11
ME-1311-10	1.07	1.12	1.15	1.18	1.10	1.16	1.08	1.12	1.09	1.16	1.13	1.11	1.14	1.12	1.11
Mean	1.08	1.11	1.14	1.16	1.10	1.13	1.12	1.12	1.10	1.14	1.13	1.11	1.11	1.11	1.12
Std. Devn.	0.0166	0.0175	0.0170	0.0228	0.0139	0.0178	0.0202	0.0081	0.0067	0.0141	0.0316	0.0085	0.0534	0.0057	0.0120
% RSD	1.54	1.58	1.49	1.97	1.27	1.58	1.81	0.72	0.62	1.24	2.81	0.77	4.83	0.51	1.07

Notes:

Pb data from laboratory 13 was removed for failing the t test.

REFERENCE MATERIAL CDN-ME-1311

Participating Laboratories:


(not in same order as listed in table of results)

Acme Analytical Laboratories Ltd., Vancouver, BC, Canada
Actlabs, Ancaster, Ontario, Canada
Actlabs, Thunder Bay, Ontario, Canada
ALS Brisbane, Australia
ALS Canada Inc., North Vancouver, BC, Canada
ALS, Loughrea, Ireland (Omac)
American Assay Laboratories Inc., Sparks, Nevada, USA
Alex Stewart Assayers, Argentina
Certimin, Lima, Peru
Genalysis, Perth, Australia
SGS, Lima, Peru
SGS Canada Inc., Burnaby, BC, Canada
Skyline Assayers and Laboratories, Nevada, USA
TSL Laboratories Ltd., Saskatoon, Saskatchewan, Canada
Ultra Trace, Perth, Australia


Legal Notice:

This certificate and the reference material described in it have been prepared with due care and attention. However CDN Resource Laboratories Ltd. or Barry Smee accept no liability for any decisions or actions taken following the use of the reference material. Our liability is limited solely to the cost of the reference material.

Certified by


Duncan Sanderson, Certified Assayer of B.C.

Geochemist


Dr. Barry Smee, Ph.D., P. Geo.