

CDN Resource Laboratories Ltd.

#2, 20148 - 102nd Avenue, Langley, B.C., Canada, V1M 4B4, Ph: 604-882-8422 Fax: 604-882-8466 (www.cdnlabs.com)

REFERENCE MATERIAL: CDN-PGMS-22

Recommended values and the "Between Lab" Two Standard Deviations

<i>Gold</i>	<i>1.23 g/t ± 0.15 g/t</i>	<i>Certified value</i>	<i>30g FA / ICP or AA</i>
<i>Platinum</i>	<i>1.36 g/t ± 0.17 g/t</i>	<i>Certified value</i>	<i>30g FA / ICP or AA</i>
<i>Palladium</i>	<i>6.15 g/t ± 0.56 g/t</i>	<i>Certified value</i>	<i>30g FA / ICP or AA</i>

PREPARED BY: CDN Resource Laboratories Ltd.

CERTIFIED BY: Duncan Sanderson, B.Sc., Licensed Assayer of British Columbia

INDEPENDENT GEOCHEMIST: Dr. Barry Smee., Ph.D., P. Geo.

DATE OF CERTIFICATION: April 12, 2012

METHOD OF PREPARATION:

The ore was supplied by Stillwater Mining Corporation from the Stillwater Complex in Montana.

The mineralogy of the Stillwater Pt/Pd ore consists of up to 1 % sulphides comprising chalcopyrite, pentlandite, pyrrhotite, ± pyrite hosted by a chromite-rich ultramafic layer. The main platinum-bearing minerals are Braggite (Pt,Pd,Ni)S, Cooperite (Pt, Pd, Ni)S as well as Isoferroplatinum (PtFe₃) and Moncheite (Pt,Pd)(Te,Bi)₂. The majority of the palladium is hosted as solid solution within the pentlandite ((Fe,Ni)₉S₈); less than 15 % as Vysotskite (Pd,Ni,Pt)S, Braggite, Cooperite and Moncheite.

This standard was prepared by combining 593 kg of the Stillwater ore (screened to -325) with 7 kg of a gold ore concentrate (screened to -325). The material was mixed for 5 days in a double-cone mixer. Splits were sent to 15 laboratories for round robin assaying.

Approximate chemical composition (by whole rock analysis) is as follows:

	Percent		Percent
SiO ₂	45.3	MgO	8.9
Al ₂ O ₃	21.8	K ₂ O	0.1
Fe ₂ O ₃	6.9	TiO ₂	0.1
CaO	12.7	LOI	2.4
Na ₂ O	1.3	S	0.1

Statistical Procedures:

The final limits were calculated after first determining if all data was compatible within a spread normally expected for similar analytical methods done by reputable laboratories. Data from any one laboratory was removed from further calculations when the mean of all analyses from that laboratory failed a t test of the global means of the other laboratories. The means and standard deviations were calculated using all remaining data. Any analysis that fell outside of the mean ±2 standard deviations was removed from the ensuing data base. The mean and standard deviations were again calculated using the remaining data. This method is different from that used by Government agencies in that the actual "between-laboratory" standard deviation is used in the calculations. This produces upper and lower limits that reflect actual individual analyses rather than a grouped set of analyses. The limits can therefore be used to monitor accuracy from individual analyses, unlike the Confidence Limits published on other standards.

Results from round-robin assaying are presented on the following page:

REFERENCE MATERIAL: CDN-PGMS-22

Assay Procedure: 30g fire assay, AA or ICP finish.

	Lab 1	Lab 2	Lab 3	Lab 4	Lab 5	Lab 6	Lab 7	Lab 8	Lab 9	Lab 10	Lab 11	Lab 12	Lab 13	Lab 14	Lab 15
SAMPLE	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t
PGMS-22-1	1.22	1.16	1.29	1.27	1.33	1.19	1.10	1.32	1.07	1.27	1.29	1.12	1.13	1.37	1.27
PGMS-22-2	1.14	1.21	1.32	1.26	1.24	1.24	1.18	1.30	1.11	1.23	1.40	1.18	1.24	1.35	1.28
PGMS-22-3	1.31	1.25	1.29	1.28	1.26	1.16	1.18	0.83	1.16	1.43	1.31	1.15	1.18	1.32	1.26
PGMS-22-4	1.26	1.22	1.26	1.27	1.21	1.18	1.16	0.98	1.24	1.27	1.25	1.11	1.15	1.27	1.36
PGMS-22-5	1.15	1.24	1.19	1.19	1.29	1.19	1.20	1.15	1.23	1.26	1.33	1.09	1.13	1.39	1.32
PGMS-22-6	1.22	1.19	1.23	1.24	1.23	1.07	1.18	1.43	1.23	1.33	1.34	1.12	1.17	1.28	1.33
PGMS-22-7	1.18	1.20	1.36	1.23	1.20	1.14	1.22	1.21	1.16	1.31	1.29	1.12	1.20	1.31	1.29
PGMS-22-8	1.20	1.26	1.31	1.23	1.34	1.19	1.22	1.18	1.17	1.24	1.30	1.15	1.10	1.28	1.40
PGMS-22-9	1.18	1.28	1.30	1.31	1.27	1.04	1.21	1.09	1.25	1.31	1.15	1.12	1.17	1.33	1.37
PGMS-22-10	1.21	1.21	1.24	1.33	1.18	1.03	1.18	1.27	1.19	1.25	1.31	1.17	1.13	1.42	1.35
Mean	1.20	1.22	1.28	1.26	1.26	1.14	1.18	1.17	1.18	1.29	1.30	1.13	1.16	1.33	1.32
Std. Dev'n	0.0501	0.0358	0.0495	0.0401	0.0536	0.0730	0.0353	0.1744	0.0579	0.0591	0.0648	0.0283	0.0408	0.0503	0.0454
%RSD	4.16	2.93	3.87	3.19	4.27	6.39	2.98	14.85	4.91	4.58	5.00	2.50	3.52	3.78	3.43
	Pt g/t	Pt g/t	Pt g/t	Pt g/t	Pt g/t	Pt g/t	Pt g/t	Pt g/t	Pt g/t	Pt g/t	Pt g/t	Pt g/t	Pt g/t	Pt g/t	Pt g/t
PGMS-22-1	1.32	1.40	1.51	1.27	1.60	1.29	1.17	1.32		1.43	1.52	1.21	1.32	1.44	1.48
PGMS-22-2	1.31	1.32	1.50	1.28	1.42	1.26	1.24	1.33		1.44	1.43	1.23	1.35	1.36	1.47
PGMS-22-3	1.33	1.34	1.44	1.25	1.44	1.30	1.27	0.85		1.41	1.56	1.28	1.35	1.46	1.52
PGMS-22-4	1.37	1.35	1.47	1.31	1.39	1.33	1.26	1.05		1.39	1.45	1.29	1.35	1.36	1.53
PGMS-22-5	1.35	1.33	1.41	1.33	1.42	1.30	1.35	1.18		1.42	1.55	1.23	1.37	1.41	1.50
PGMS-22-6	1.34	1.34	1.43	1.26	1.36	1.24	1.22	1.33		1.41	1.35	1.27	1.31	1.41	1.53
PGMS-22-7	1.33	1.39	1.46	1.26	1.40	1.27	1.37	1.34		1.39	1.38	1.30	1.39	1.40	1.52
PGMS-22-8	1.29	1.41	1.45	1.27	1.51	1.26	1.33	1.29		1.39	1.64	1.30	1.28	1.44	1.54
PGMS-22-9	1.37	1.44	1.49	1.37	1.45	1.28	1.39	1.14		1.40	1.62	1.25	1.26	1.42	1.51
PGMS-22-10	1.34	1.38	1.46	1.39	1.43	1.20	1.26	1.24		1.45	1.59	1.25	1.27	1.37	1.54
Mean	1.33	1.37	1.46	1.30	1.44	1.27	1.29	1.20		1.41	1.51	1.26	1.33	1.41	1.51
Std. Dev'n	0.0258	0.0397	0.0316	0.0490	0.0683	0.0339	0.0711	0.1590		0.0216	0.1001	0.0318	0.0443	0.0350	0.0250
%RSD	1.94	2.90	2.16	3.77	4.74	2.66	5.53	13.20		1.53	6.64	2.52	3.34	2.49	1.65
	Pd g/t	Pd g/t	Pd g/t	Pd g/t	Pd g/t	Pd g/t	Pd g/t	Pd g/t	Pd g/t	Pd g/t	Pd g/t	Pd g/t	Pd g/t	Pd g/t	Pd g/t
PGMS-22-1	6.05	5.98	6.67	6.05	6.76	6.03	5.57	6.01		6.24	6.00	5.75	5.82	6.50	6.90
PGMS-22-2	6.22	6.05	6.66	6.13	6.15	6.13	5.88	5.94		6.37	6.12	5.69	5.71	6.44	6.91
PGMS-22-3	6.21	5.94	6.67	6.07	6.37	6.28	5.83	3.90		6.36	6.31	5.82	6.15	6.51	7.06
PGMS-22-4	6.27	5.94	6.81	6.12	6.35	6.20	6.11	4.75		6.24	6.20	5.76	5.88	6.43	7.10
PGMS-22-5	6.21	6.03	6.73	6.03	6.29	6.04	6.29	5.31		6.30	6.41	5.65	6.00	6.61	7.08
PGMS-22-6	6.17	5.92	6.70	6.10	6.24	5.91	5.96	5.64		6.24	6.13	5.73	6.06	6.58	7.21
PGMS-22-7	6.17	5.89	6.77	6.08	6.12	6.12	6.43	5.87		6.20	6.16	5.91	6.07	6.55	7.02
PGMS-22-8	6.16	5.92	6.90	6.06	6.58	6.07	6.42	5.83		6.22	6.42	5.87	5.75	6.57	7.03
PGMS-22-9	6.19	5.94	6.79	6.08	6.45	6.09	6.28	5.06		6.14	6.23	5.73	5.73	6.52	7.08
PGMS-22-10	6.18	6.04	6.54	6.31	6.35	5.86	6.25	5.72		6.25	6.03	5.79	5.77	6.50	7.16
Mean	6.18	5.97	6.72	6.10	6.37	6.07	6.10	5.40		6.26	6.20	5.77	5.89	6.52	7.06
Std. Dev'n	0.0568	0.0566	0.0996	0.0781	0.1936	0.1239	0.2837	0.6688		0.0703	0.1460	0.0796	0.1626	0.0582	0.0966
%RSD	0.92	0.95	1.48	1.28	3.04	2.04	4.65	12.38		1.12	2.35	1.38	2.76	0.89	1.37

**Note: Pt data from Lab 11 was excluded for failing the t test.
Pd data from Lab 15 was excluded for failing the t test.**

One laboratory did not supply Pt, Pd data.

REFERENCE MATERIAL: CDN-PGMS-22

Participating Laboratories:


(not in same order as listed in table of results)

Acme Analytical Laboratories Ltd., Vancouver, B.C., Canada
Activation Laboratories Ltd., Ancaster, Ontario, Canada
Activation Laboratories Ltd., Thunder Bay, Ontario, Canada
AGAT, Mississauga, Ontario
Alex Stewart Argentina SA
ALS Chemex Laboratories, North Vancouver, B.C., Canada
ALS Brisbane, Australia
American Assay Laboratories, Nevada, USA
Genalysis Laboratory Services Pty. Ltd., Perth, Australia
Labtium, Finland
SGS, Lima, Peru
SGS, Vancouver, B.C., Canada
Skyline Assayers & Laboratories, Arizona, USA
TSL Laboratories, Saskatoon, SK, Canada
Ultra Trace Analytical Laboratories, Perth, Australia

Legal Notice:


This certificate and the reference material described in it have been prepared with due care and attention. However CDN Resource Laboratories Ltd. or Barry Smee accept no liability for any decisions or actions taken following the use of the reference material. Our liability is limited solely to the cost of the reference material.

Certified by



Duncan Sanderson, Certified Assayer of B.C.

Geochemist



Barry Smee, Ph.D., P. Geo.