

CDN Resource Laboratories Ltd.

10945-B River Road, Delta, B.C., V4C 2R8, Ph: 604-540-2233, Fax: 604-588-3960

STANDARD REFERENCE MATERIAL: CDN-BL2

Recommended values:

Gold concentration: < 0.01 g/t

Platinum concentration: < 0.01 g/t

Palladium concentration: < 0.01 g/t

PREPARED BY: CDN Resource Laboratories Ltd.
CERTIFIED BY: Duncan Sanderson, B.Sc., Licensed Assayer of British Columbia
INDEPENDENT GEOCHEMIST: Dr. Barry Smee., Ph. D., P. Geo.
DATE OF CERTIFICATION: March 15, 2006

ORIGIN OF REFERENCE MATERIAL:

Standard CDN-BL2 was prepared using a blank granitic material.

METHOD OF PREPARATION:

The granitic material was dried, crushed, pulverized and then passed through a 200 mesh screen. The +200 material was discarded. The -200 (<75 micron) material was mixed for 5 days in a rotary mixer. Splits were taken and sent to 6 commercial laboratories for round robin assaying. Round robin results are displayed below:

APPROXIMATE CHEMICAL COMPOSITION:

	Percent			Percent
SiO ₂	69.6		Na ₂ O	4.5
Al ₂ O ₃	14.0		MgO	0.9
Fe ₂ O ₃	4.7		K ₂ O	1.9
CaO	2.4		TiO ₂	0.4
MnO	0.1		LOI	0.9

Statistical Procedures:

There was no statistical analysis performed on the data. All analytical results were less than the recommended values.

Participating Laboratories: (not in same order as table of assays)

Acme Analytical Laboratories Ltd.
Assayers Canada Ltd., Vancouver
ALS Chemex Laboratories, North Vancouver
International Plasma Laboratories Ltd., Vancouver
Teck Cominco - Global Discovery Laboratory, Vancouver
TSL Laboratories, Saskatoon

Assay Procedure: assays were fire assay, AA or ICP finish on 30g samples.


STANDARD REFERENCE MATERIAL: CDN-BL2

	Lab. 1	Lab. 2	Lab. 3	Lab. 4	Lab. 5	Lab. 6
Sample	Au ppb	Au ppb	Au ppb	Au ppb	Au ppb	Au ppb
CDN-BL2-1	< 10	< 10	<2	2	< 5	5
CDN-BL2-2	< 10	< 10	<2	1	< 5	6
CDN-BL2-3	< 10	< 10	<2	1	< 5	4
CDN-BL2-4	< 10	< 10	<2	1	< 5	5
CDN-BL2-5	< 10	< 10	<2	1	< 5	5
CDN-BL2-6	< 10	< 10	<2	1	< 5	3
CDN-BL2-7	< 10	< 10	<2	2	< 5	4
CDN-BL2-8	< 10	< 10	<2	1	< 5	4
CDN-BL2-9	< 10	< 10	<2	1	< 5	7
CDN-BL2-10	< 10	< 10	<2	1	< 5	4
	Pt ppb	Pt ppb	Pt ppb	Pt ppb	Pt ppb	Pt ppb
CDN-BL2-1	< 10	< 10	4	< 5	< 10	< 5
CDN-BL2-2	< 10	< 10	3	< 5	< 10	< 5
CDN-BL2-3	< 10	< 10	< 2	< 5	< 10	< 5
CDN-BL2-4	< 10	< 10	< 2	< 5	< 10	< 5
CDN-BL2-5	< 10	10	3	< 5	< 10	< 5
CDN-BL2-6	< 10	< 10	< 2	< 5	< 10	< 5
CDN-BL2-7	< 10	< 10	3	< 5	< 10	< 5
CDN-BL2-8	< 10	< 10	< 2	< 5	< 10	< 5
CDN-BL2-9	< 10	< 10	< 2	< 5	< 10	< 5
CDN-BL2-10	< 10	< 10	2	7	< 10	< 5
	Pd ppb	Pd ppb	Pd ppb	Pd ppb	Pd ppb	Pd ppb
CDN-BL2-1	< 10	< 10	2	1	< 5	< 2
CDN-BL2-2	< 10	< 10	5	< 1	< 5	< 2
CDN-BL2-3	< 10	< 10	<2	1	< 5	< 2
CDN-BL2-4	< 10	10	<2	< 1	< 5	< 2
CDN-BL2-5	< 10	< 10	2	< 1	< 5	< 2
CDN-BL2-6	< 10	< 10	8	< 1	< 5	< 2
CDN-BL2-7	< 10	< 10	3	1	< 5	< 2
CDN-BL2-8	< 10	< 10	5	< 1	< 5	< 2
CDN-BL2-9	< 10	< 10	2	1	< 5	< 2
CDN-BL2-10	< 10	< 10	2	< 1	< 5	< 2


Legal Notice:

This certificate and the reference material described in it have been prepared with due care and attention. However CDN Resource Laboratories Ltd. nor Barry Smee accept any liability for any decisions or actions taken following the use of the reference material. Our liability is limited solely to the cost of the reference material.

Certified by


Duncan Sanderson, Certified Assayer of B.C.

Geochemist


Dr. Barry Smee, Ph.D., P. Geo.