

CDN Resource Laboratories Ltd.

#2, 20148 – 102nd Ave, Langley, B.C., Canada, V1M 4B4, 604-882-8422, Fax: 604-882-8466 (www.cdnlabs.com)

REFERENCE MATERIAL: CDN-GS-51

Recommended value and the "Between Laboratory" two standard deviations

| | | | |
|------|----------------------|-----------------|----------------------|
| Gold | 51.12 g/t ± 1.79 g/t | Certified value | 30g FA / Gravimetric |
|------|----------------------|-----------------|----------------------|

PREPARED BY: CDN Resource Laboratories Ltd.
CERTIFIED BY: Duncan Sanderson, B.Sc., Licensed Assayer of British Columbia
INDEPENDENT GEOCHEMIST: Dr. Barry Smee., Ph.D., P. Geo.
DATE OF CERTIFICATION: October 31st, 2018

ORIGIN OF REFERENCE MATERIAL:

Standard CDN-GS-51 was prepared by combining several different siliceous ores with low sulphide content, blended with 30 kg of high-grade ore supplied by Teuton Resources from their Clone gold property in B.C., Canada. Mineralization of Clone gold property is localized within highly silicified semi-massive to massive specular hematite. Gold occurs as fine disseminations and is associated with the oxide mineralization. The major lithology is light grey to green andesitic pyroclastic intercalated with fine grained to aphanitic andesite. Clasts are sub angular to angular, matrix supported, and range in size from 1-3cm. Quartz-calcite stockwork pervades the unit in moderate abundance

METHOD OF PREPARATION:

Reject ore material was dried, crushed, pulverized and then passed through a 270-mesh screen. The +270 material was discarded. The -270 material was mixed for 5 days in a double-cone blender. Splits were taken and sent to 15 commercial laboratories for round robin assaying.

ASSAY PROCEDURES:

Au: 30 gr Fire assay pre-concentration, Gravimetric finish.
Whole rock analysis and 30 element ICP analysis (4-acid digestion) were also conducted on 5 samples.

APPROXIMATE CHEMICAL COMPOSITION (by whole rock analysis):

| | Percent | | Percent |
|--------------------------------|---------|-------------------|---------|
| SiO ₂ | 60.3 | Na ₂ O | 2.7 |
| Al ₂ O ₃ | 11.7 | MgO | 3.9 |
| Fe ₂ O ₃ | 10.2 | K ₂ O | 1.5 |
| CaO | 3.6 | TiO ₂ | 0.3 |
| MnO | 0.1 | LOI | 3.9 |
| Total S | 2.0 | Total C | 0.4 |

STATISTICAL PROCEDURES:

The final limits were calculated after first determining if all data was compatible within a spread normally expected for similar analytical methods done by reputable laboratories. Data from any one laboratory was removed from further calculations when the mean of all analyses from that laboratory failed a t test of the global means of the other laboratories. The mean and standard deviation were calculated using all remaining data. Any analysis that fell outside of the mean ±2 standard deviations was removed from the ensuing data base. The mean and standard deviations were again calculated using the remaining data. This method is different from that used by Government agencies in that the actual "between-laboratory" standard deviation is used in the calculations. This produces upper and lower limits that reflect actual individual analyses rather than a grouped set of analyses. The limits can therefore be used to monitor accuracy from individual analyses, unlike the Confidence Limits published on other standards.

Our certified gold values are based on 30 g Fire Assay determinations. For optimal results, we strongly recommend you assay our standards with similar methods using "at least" 30 g of material. Using a smaller sample weight may result in erratic values.

RESULTS FROM ROUND ROBIN ASSAYING:

| Fire Assay Gravimetric Finish | Lab 1 | Lab 2 | Lab 3 | Lab 4 | Lab 5 | Lab 6 | Lab 7 | Lab 8 | Lab 9 | Lab 10 | Lab 11 | Lab 12 | Lab 13 | Lab 14 | Lab 15 |
|-------------------------------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|
| | Au g/t | Au g/t | Au g/t | Au g/t | Au g/t | Au g/t | Au g/t | Au g/t | Au g/t | Au g/t | Au g/t | Au g/t | Au g/t | Au g/t | Au g/t |
| GS-51-1 | 51.5 | 50.0 | 51.2 | 50.3 | 49.67 | 52.05 | 49.44 | 51.15 | 50.43 | 52.32 | 50.20 | 50.98 | 50.23 | 51.1 | 52.50 |
| GS-51-2 | 52.2 | 51.4 | 49.5 | 51.4 | 49.32 | 52.03 | 51.45 | 50.15 | 51.19 | 51.31 | 51.67 | 50.80 | 51.97 | 51.3 | 51.80 |
| GS-51-3 | 52.3 | 51.7 | 51.2 | 51.2 | 52.03 | 50.81 | 49.31 | 51.45 | 51.80 | 52.64 | 50.23 | 50.78 | 51.39 | 50.4 | 53.30 |
| GS-51-4 | 51.4 | 50.0 | 52.4 | 51.6 | 50.26 | 51.20 | 50.17 | 51.65 | 51.57 | 52.07 | 52.03 | 51.05 | 52.20 | 51.9 | 53.20 |
| GS-51-5 | 53.4 | 50.6 | 51.1 | 51.4 | 51.76 | 51.26 | 50.76 | 51.55 | 51.73 | 51.23 | 50.23 | 50.70 | 50.60 | 51.7 | 52.20 |
| GS-51-6 | 50.3 | 50.3 | 50.0 | 53.6 | 49.38 | 50.29 | 51.12 | 50.40 | 51.83 | 52.12 | 50.31 | 51.94 | 49.04 | 48.2 | 51.50 |
| GS-51-7 | 51.7 | 52.9 | 51.0 | 51.8 | 50.63 | 50.44 | 48.95 | 51.50 | 51.80 | 51.41 | 51.62 | 50.64 | 50.17 | 50.3 | 53.10 |
| GS-51-8 | 54.3 | 52.1 | 52.1 | 52.0 | 50.40 | 51.09 | 51.58 | 51.25 | 50.67 | 51.72 | 50.10 | 51.61 | 52.34 | 50.2 | 53.50 |
| GS-51-9 | 53.7 | 52.5 | 51.1 | 51.8 | 51.34 | 51.42 | 50.20 | 51.40 | 50.77 | 51.63 | 51.93 | 50.11 | 50.35 | 49.6 | 51.80 |
| GS-51-10 | 52.5 | 50.9 | 49.7 | 51.7 | 49.63 | 50.27 | 49.18 | 50.90 | 51.53 | 51.25 | 50.98 | 50.75 | 50.42 | 50.1 | 52.50 |
| Mean | 52.3 | 51.2 | 50.9 | 51.7 | 50.44 | 51.09 | 50.22 | 51.14 | 51.33 | 51.77 | 50.93 | 50.94 | 50.87 | 50.5 | 52.54 |
| Std. Dev. | 1.203 | 1.044 | 0.952 | 0.824 | 0.988 | 0.647 | 0.977 | 0.508 | 0.530 | 0.494 | 0.804 | 0.514 | 1.065 | 1.095 | 0.711 |
| % RSD | 2.30 | 2.04 | 1.87 | 1.60 | 1.96 | 1.27 | 1.95 | 0.99 | 1.03 | 0.95 | 1.58 | 1.01 | 2.09 | 2.17 | 1.35 |


PARTICIPATING LABORATORIES: (not in same order as table of assays)

| | |
|---|--|
| Argetest, Ankara, Turkey | Certimin S.A., Lima, Peru |
| ALS Canada, North Vancouver, BC, Canada | MS Analytical, Langley, BC, Canada |
| ALS, Loughrea, Ireland | SGS, Vancouver, BC, Canada |
| ALS, Lima, Peru | SGS, Lima, Peru |
| ALS, Perth Australia | SGS, Lakefield, Ontario, Canada |
| ALS, Reno, USA | Sky Line, Arizona, USA |
| Bureau Veritas, Perth, Australia | TSL Laboratories Ltd., Saskatoon, SK, Canada |
| Bureau Veritas, Vancouver, BC, Canada | |

LEGAL NOTICE:

This certificate and the reference material described in it have been prepared with due care and attention. However, CDN Resource Laboratories Ltd. nor Barry Smee accept any liability for any decisions or actions taken following the use of the reference material. Our liability is limited solely to the cost of the reference material.

Certified by 
 Duncan Sanderson, Certified Assayer of B.C.

Geochemist 
 Dr. Barry Smee, Ph.D., P. Geo.