

CDN Resource Laboratories Ltd.

#2, 20148 – 102nd Avenue, Langley, B.C., Canada, V1M 4B4, 604-882-8422, Fax: 604-882-8466 (www.cdnlabs.com)

REFERENCE MATERIAL: CDN-GS-7G

Recommended value and the "Between Laboratory" two standard deviations

Gold	7.19 g/t	±	0.37 g/t	30 g FA, instrumental	Certified value
Gold	7.15 g/t	±	0.40 g/t	30 g FA, gravimetric	Certified value

Note: Standards with an RSD of near or less than 5% are certified; RSD's of between 5% and 15% are Provisional; RSD's over 15% are Indicated. Provisional and Indicated values cannot be used to monitor accuracy with a high degree of certainty.

The certified value and between lab 2SD calculated for each element are based on specific analytical procedures. It is inappropriate to apply them to other techniques.

PREPARED BY: CDN Resource Laboratories Ltd.
CERTIFIED BY: Duncan Sanderson, B.Sc., Licensed Assayer of British Columbia
INDEPENDENT GEOCHEMIST: Dr. Barry Smee., Ph.D., P. Geo.
DATE OF CERTIFICATION: June 21, 2016

ORIGIN OF REFERENCE MATERIAL:

Standard CDN-GS-7G was prepared using 730 kg of low grade granitic ore with 70 kg of gold bearing ore.

METHOD OF PREPARATION:

Reject ore material was dried, crushed, pulverized and then passed through a 270 mesh screen. The +270 material was discarded. The -270 material was mixed for 5 days in a double-cone blender. Splits were taken and sent to 15 commercial laboratories for round robin assaying. Round robin results are displayed below:

	Lab 1	Lab 2	Lab 3	Lab 4	Lab 5	Lab 6	Lab 7	Lab 8	Lab 9	Lab 10	Lab 11	Lab 12	Lab 13	Lab 14	Lab 15
Instrumental	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t
GS-7G-1	7.21	7.56	7.07	6.88	7.30	6.94	7.17	7.32	7.17	6.66	7.18	7.45	7.29	7.22	7.07
GS-7G-2	7.51	7.58	7.20	6.98	7.25	6.68	7.27	7.42	7.30	7.25	7.06	7.52	7.42	7.14	7.01
GS-7G-3	7.23	7.59	7.17	7.00	7.42	7.03	7.36	7.11	7.34	7.03	6.87	7.39	7.37	7.17	6.95
GS-7G-4	7.20	7.50	7.35	6.74	7.41	7.06	7.23	7.24	7.21	6.90	7.11	7.37	7.13	7.02	7.07
GS-7G-5	7.61	7.50	7.12	6.80	7.21	7.26	7.00	7.18	6.99	6.98	7.14	7.16	7.33	7.01	7.06
GS-7G-6	7.22	7.49	7.01	7.05	7.34	6.91	7.20	7.11	7.15	6.86	7.15	7.64	7.30	6.97	7.08
GS-7G-7	7.15	7.44	7.05	7.03	7.29	6.83	7.20	7.12	7.21	7.00	6.71	7.49	7.14	7.11	7.16
GS-7G-8	7.04	7.46	7.32	7.03	7.35	7.15	7.22	7.28	7.40	7.20	7.13	7.42	7.49	6.94	7.15
GS-7G-9	7.14	7.48	7.14	6.79	7.29	7.19	7.23	7.45	7.22	7.28	6.95	7.70	7.30	6.93	7.14
GS-7G-10	7.32	7.52	6.95	6.88	7.24	7.15	7.08	7.16	7.06	7.00	7.07	7.52	7.40	6.94	6.99
Mean	7.26	7.51	7.14	6.92	7.31	7.02	7.19	7.24	7.21	7.02	7.04	7.47	7.32	7.05	7.07
Std. Dev'n	0.1738	0.0495	0.1280	0.1145	0.0709	0.1802	0.0982	0.1259	0.1229	0.1900	0.1497	0.1498	0.1145	0.1066	0.0699
%RSD	2.39	0.66	1.79	1.65	0.97	2.57	1.37	1.74	1.70	2.71	2.13	2.01	1.56	1.51	0.99
Gravimetric	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t
GS-7G-1	7.37	7.07	6.93	6.90	7.53	7.13	7.39	6.84	7.41	6.47	7.19	7.28	7.51	6.80	7.60
GS-7G-2	7.29	7.12	7.12	7.30	7.29	6.88	7.54	7.06	7.44	6.92	6.79	7.33	7.35	6.80	7.37
GS-7G-3	7.17	7.11	7.07	6.90	7.23	6.93	7.42	7.10	7.49	6.58	6.87	7.05	7.32	6.60	7.30
GS-7G-4	6.98	7.15	6.97	7.20	7.33	7.22	7.25	6.88	7.33	7.06	7.03	7.12	7.26	7.00	7.63
GS-7G-5	7.26	7.10	6.96	7.10	7.39	7.15	7.11	6.95	7.10	7.06	7.15	7.17	7.17	6.50	7.57
GS-7G-6	7.07	7.08	6.96	7.10	7.36	7.14	7.25	7.35	7.13	7.14	7.15	6.98	7.34	6.70	7.43
GS-7G-7	7.20	7.23	7.33	6.90	7.51	6.87	7.34	6.96	7.38	7.21	6.69	7.18	7.34	6.70	7.67
GS-7G-8	7.22	7.11	6.70	7.10	7.30	6.91	7.33	6.82	7.35	7.06	6.95	7.23	7.37	6.90	7.57
GS-7G-9	7.13	7.16	7.05	7.00	7.34	7.23	7.10	7.29	7.20	7.15	7.07	7.17	7.59	7.20	7.30
GS-7G-10	7.17	7.09	6.78	7.00	7.34	7.08	6.91	7.14	7.02	7.03	7.09	7.13	7.24	6.90	7.40
Mean	7.19	7.12	6.99	7.05	7.36	7.05	7.26	7.04	7.29	6.97	7.00	7.16	7.35	6.81	7.48
Std. Dev'n	0.1111	0.0473	0.1752	0.1354	0.0939	0.1421	0.1834	0.1829	0.1608	0.2475	0.1673	0.1031	0.1235	0.2025	0.1394
%RSD	1.55	0.66	2.51	1.92	1.28	2.02	2.53	2.60	2.21	3.55	2.39	1.44	1.68	2.97	1.86

APPROXIMATE CHEMICAL COMPOSITION (by whole rock analysis):

	Percent		Percent
SiO ₂	60.0	Na ₂ O	2.9
Al ₂ O ₃	15.9	MgO	2.6
Fe ₂ O ₃	9.2	K ₂ O	1.8
CaO	5.5	TiO ₂	0.5
MnO	0.1	LOI	1.1
Total S	<0.1	Total C	<0.1

Statistical Procedures:

The final limits were calculated after first determining if all data was compatible within a spread normally expected for similar analytical methods done by reputable laboratories. Data from any one laboratory was removed from further calculations when the mean of all analyses from that laboratory failed a t test of the global means of the other laboratories. The mean and standard deviation were calculated using all remaining data. Any analysis that fell outside of the mean ± 2 standard deviations was removed from the ensuing data base. The mean and standard deviations were again calculated using the remaining data. This method is different from that used by Government agencies in that the actual "between-laboratory" standard deviation is used in the calculations. This produces upper and lower limits that reflect actual individual analyses rather than a grouped set of analyses. The limits can therefore be used to monitor accuracy from individual analyses, unlike the Confidence Limits published on other standards.

Our certified gold values are based on 30 g Fire Assay determinations. For optimal results, we strongly recommend you assay our standards with similar methods using "at least" 30 g of material. Using a smaller sample weight may result in erratic values.

Participating Laboratories: (not in same order as table of assays)

- Actlabs, Ancaster, Ontario, Canada
- Actlabs, Thunder Bay, Ontario, Canada
- AGAT Labs, Mississauga, Ontario, Canada
- ALS Canada, North Vancouver, British Columbia, Canada
- ALS Reno, Sparks, Nevada, USA
- American Assay Laboratories Inc., Sparks, Nevada, USA
- Argetest, Ankara, Turkey
- Bureau Veritas (Acme), Vancouver, British Columbia, Canada
- Bureau Veritas (Ultra Trace), Perth, Australia
- Certimin, Lima, Peru
- Labtium, Finland
- Met-Solve Analytical Services, Langley, British Columbia, Canada
- SGS, Lakefield, Ontario, Canada
- SGS, Lima, Peru
- SGS, Vancouver, British Columbia, Canada

Legal Notice:

This certificate and the reference material described in it have been prepared with due care and attention. However CDN Resource Laboratories Ltd. nor Barry Smee accept any liability for any decisions or actions taken following the use of the reference material. Our liability is limited solely to the cost of the reference material.

Certified by *Duncan Sanderson*
 Duncan Sanderson, Certified Assayer of B.C.

Geochemist *BW Smee*
 Dr. Barry Smee, Ph.D., P. Geo.