

CDN Resource Laboratories Ltd.

#2, 20148 – 102nd Avenue, Langley, B.C., Canada, V1M 4B4, 604-882-8422, Fax: 604-882-8466 (www.cdnlabs.com)

GOLD ORE REFERENCE MATERIAL CDN-GS-4B

Recommended value and the "Between Laboratory" two standard deviations

Gold concentration: 3.77 ± 0.35 g/t

PREPARED BY: CDN Resource Laboratories Ltd.
CERTIFIED BY: Duncan Sanderson, B.Sc., Licensed Assayer of British Columbia
INDEPENDENT GEOCHEMIST: Dr. Barry Smee., Ph.D., P. Geo.
DATE OF CERTIFICATION: April 8, 2010

ORIGIN OF REFERENCE MATERIAL:

Standard CDN-GS-4B was prepared using ore supplied by Teuton Resources from their Clone gold property in B.C., Canada. Mineralization is localized within highly silicified semi-massive to massive specular hematite. The gold occurs as fine disseminations and is associated with the oxide mineralization. The major lithology is observed to be light grey to green andesitic pyroclastics intercalated with fine grained to aphanitic andesite. Clasts are subangular to angular, matrix supported, and range in size from 1-3cm. Quartz-calcite stockwork pervades the unit in moderate abundance. 19 kg of this ore was blended with 781 kg of a blank granitic ore.

METHOD OF PREPARATION:

Reject ore material was dried, crushed, pulverized and then passed through a 270 mesh screen. The +270 material was discarded. The -270 material was mixed for 5 days in a double-cone blender. Splits were taken and sent to 14 commercial laboratories for round robin assaying. Round robin results are displayed below:

	Lab 1	Lab 2	Lab 3	Lab 4	Lab 5	Lab 6	Lab 7	Lab 8	Lab 9	Lab 10	Lab 11	Lab 12	Lab 13	Lab 14
SAMPLE	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t
CDN-GS-4B-1	3.90	3.90	4.26	3.62	3.47	3.70	3.61	3.76	3.84	3.85	3.83	3.92	3.78	3.70
CDN-GS-4B-2	3.49	3.83	4.06	3.68	3.57	3.69	3.62	3.85	3.70	3.57	3.65	3.69	3.81	3.88
CDN-GS-4B-3	3.77	3.92	4.10	3.73	3.52	3.91	3.65	3.40	3.54	4.04	3.85	3.93	3.69	4.18
CDN-GS-4B-4	3.83	3.89	4.14	3.70	3.48	3.55	3.90	3.42	3.98	3.72	3.93	3.88	3.56	3.87
CDN-GS-4B-5	3.85	3.83	4.17	3.82	3.39	3.85	3.80	3.51	4.01	3.49	3.96	4.02	3.78	3.94
CDN-GS-4B-6	3.74	4.20	4.24	3.67	3.29	3.65	3.83	3.34	4.06	3.90	3.72	3.91	3.84	4.17
CDN-GS-4B-7	3.81	4.13	3.94	3.73	3.42	3.54	3.60	3.35	3.80	3.59	3.86	3.95	3.80	3.94
CDN-GS-4B-8	4.10	4.08	4.00	3.68	3.56	3.74	3.48	3.62	3.67	3.85	4.02	3.91	3.67	3.90
CDN-GS-4B-9	3.98	4.04	4.25	3.66	3.57	3.67	3.69	3.76	4.09	3.89	3.61	4.01	3.77	3.92
CDN-GS-4B-10	3.59	4.15	4.05	3.59	3.59	3.61	3.80	3.28	4.06	3.77	3.77	4.02	3.94	3.73
Mean	3.81	4.00	4.12	3.69	3.49	3.69	3.70	3.53	3.88	3.77	3.82	3.92	3.76	3.92
Std. Dev'n	0.1765	0.1389	0.1103	0.0637	0.0950	0.1188	0.1301	0.2046	0.1931	0.1733	0.1332	0.0964	0.1030	0.1563
%RSD	4.64	3.47	2.68	1.73	2.72	3.22	3.52	5.80	4.98	4.60	3.49	2.46	2.74	3.98

Note: results from Lab. 3 were removed for failing the t test.

Assay Procedure: all assays were fire assay, ICP finish on 30g samples.

APPROXIMATE CHEMICAL COMPOSITION:

	Percent		Percent
SiO ₂	65.8	Na ₂ O	2.5
Al ₂ O ₃	13.2	MgO	1.7
Fe ₂ O ₃	6.6	K ₂ O	2.9
CaO	3.2	TiO ₂	0.3
MnO	0.1	LOI	1.8
S	0.6	C	0.2

GOLD ORE REFERENCE MATERIAL: CDN-GS-4B

Statistical Procedures:

The final limits were calculated after first determining if all data was compatible within a spread normally expected for similar analytical methods done by reputable laboratories. Data from any one laboratory was removed from further calculations when the mean of all analyses from that laboratory failed a t test of the global means of the other laboratories. The mean and standard deviation were calculated using all remaining data. Any analysis that fell outside of the mean ± 2 standard deviations was removed from the ensuing data base. The mean and standard deviations were again calculated using the remaining data. This method is different from that used by Government agencies in that the actual "between-laboratory" standard deviation is used in the calculations. This produces upper and lower limits that reflect actual individual analyses rather than a grouped set of analyses. The limits can therefore be used to monitor accuracy from individual analyses, unlike the Confidence Limits published on other standards.

Participating Laboratories:


(not in same order as table of assays)

Acme Analytical Laboratories Ltd., Vancouver, Canada
Activation Laboratories, Ancaster, Ontario, Canada
Activation Laboratories, Thunder Bay, Ontario, Canada
AGAT Laboratories Ltd., Ontario, Canada
ALS Chemex, North Vancouver, Canada
ASA Omac, Ireland
Assayers Canada Ltd., Vancouver, Canada
Eco-Tech, Kamloops, Canada
Genalysis Lab. Services, Australia
Labtium Inc., Finland
SGS – Toronto, Canada
SGS – Durango, Mexico
TSL Laboratories Ltd., Saskatoon, Canada
Ultra Trace Pty. Ltd., Australia


Legal Notice:

This certificate and the reference material described in it have been prepared with due care and attention. However CDN Resource Laboratories Ltd. nor Barry Smee accept any liability for any decisions or actions taken following the use of the reference material. Our liability is limited solely to the cost of the reference material.

Certified by


Duncan Sanderson, Certified Assayer of B.C.

Geochemist


Dr. Barry Smee, Ph.D., P. Geo.