

# CDN Resource Laboratories Ltd.

Unit 2 - 20148, 102nd Avenue, Langley, B.C., Canada, V1M 4B4, Ph: 604-882-8422 Fax: 604-882-8466  
(www.cdnlabs.com)

## ORE REFERENCE STANDARD: CDN-HC-2

Recommended values and the "Between Lab" Two Standard Deviations

<i>Gold</i>	<i>1.67</i>	<i>±</i>	<i>0.12 g/t</i>
<i>Silver</i>	<i>15.3</i>	<i>±</i>	<i>1.4 g/t</i>
<i>Copper</i>	<i>4.63</i>	<i>±</i>	<i>0.26 %</i>
<i>Lead</i>	<i>0.476</i>	<i>±</i>	<i>0.036 %</i>
<i>Zinc</i>	<i>0.259</i>	<i>±</i>	<i>0.014 %</i>

**PREPARED BY:** CDN Resource Laboratories Ltd.  
**CERTIFIED BY:** Duncan Sanderson, B.Sc., Licensed Assayer of British Columbia  
**INDEPENDENT GEOCHEMIST:** Dr. Barry Smee., Ph.D., P. Geo.  
**DATE OF CERTIFICATION:** April 11, 2008

### **METHOD OF PREPARATION:**

Reject ore material was dried, crushed, pulverized and then passed through a 200 mesh screen. The +200 material was discarded. The -200 material was mixed for 5 days in a double-cone mixer. Splits were taken and sent to twelve laboratories for round robin assaying. The material has been packaged in nominal 100g (or 60g) lots in tin-top kraft bags which have been individually vacuum-sealed in nylon bags.

### **ORIGIN OF REFERENCE MATERIAL:**

Standard CDN-HC-2 was made by compositing 655 kg of ore from the Kenrich Eskay Creek property with 115 kg of three high sulphide concentrates.

### **Approximate chemical composition is as follows:**

	Percent		Percent
SiO <sub>2</sub>	38.0	MgO	6.1
Al <sub>2</sub> O <sub>3</sub>	9.6	K <sub>2</sub> O	0.9
Fe <sub>2</sub> O <sub>3</sub>	24.4	TiO <sub>2</sub>	0.8
CaO	3.0	LOI	11.1
Na <sub>2</sub> O	1.3	S	14.7

### **Statistical Procedures:**

The final limits were calculated after first determining if all data was compatible within a spread normally expected for similar analytical methods done by reputable laboratories. Data from any one laboratory was removed from further calculations when the mean of all analyses from that laboratory failed a t test of the global means of the other laboratories. The means and standard deviations were calculated using all remaining data. Any analysis that fell outside of the mean  $\pm 2$  standard deviations was removed from the ensuing data base. The mean and standard deviations were again calculated using the remaining data. This method is different from that used by Government agencies in that the actual "between-laboratory" standard deviation is used in the calculations. This produces upper and lower limits that reflect actual individual analyses rather than a grouped set of analyses. The limits can therefore be used to monitor accuracy from individual analyses, unlike the Confidence Limits published on other standards.

### **Assay Procedures:**

**Au:** Fire assay pre-concentration, AA or ICP finish (10g sub-sample).  
**Ag, Cu, Pb, Zn:** 4-acid digestion, AA or ICP finish.

## STANDARD REFERENCE MATERIAL CDN-HC-2

### Results from round-robin assaying:

	Lab 1	Lab 2	Lab 3	Lab 4	Lab 5	Lab 6	Lab 7	Lab 8	Lab 9	Lab 10	Lab 11	Lab 12
	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	
CDN-HC2-1	1.67	1.80	1.64	1.625	1.65	1.61	1.81	1.77	1.62	1.64	1.58	1.72
CDN-HC2-2	1.57	1.64	1.69	1.655	1.72	1.48	1.59	1.70	1.64	1.61	1.60	1.66
CDN-HC2-3	1.62	1.69	1.68	1.610	1.84	1.57	1.76	1.73	1.59	1.68	1.73	1.66
CDN-HC2-4	1.71	1.84	1.64	1.670	1.67	1.53	1.60	1.74	1.71	1.72	1.64	1.58
CDN-HC2-5	1.77	1.58	1.66	1.680	1.74	1.73	1.70	1.78	1.63	1.72	1.69	1.58
CDN-HC2-6	1.58	1.92	1.70	1.705	1.86	1.57	1.81	1.63	1.72	1.62	1.54	1.58
CDN-HC2-7	1.72	1.82	1.68	1.765	1.74	1.67	1.67	1.78	1.65	1.60	1.65	1.66
CDN-HC2-8	1.60	1.78	1.65	1.800	1.71	1.71	1.69	1.69	1.63	1.72	1.78	1.63
CDN-HC2-9	1.62	1.89	1.64	1.660	1.67	1.50	1.59	1.72	1.62	1.65	1.74	1.62
CDN-HC2-10	1.74	1.73	1.69	1.645	1.68	1.67	1.65	1.77	1.71	1.59	1.57	1.62
Mean	1.66	1.77	1.67	1.68	1.73	1.60	1.69	1.73	1.65	1.66	1.65	1.63
Std. Devn.	0.0715	0.1087	0.0236	0.0601	0.0713	0.0881	0.0837	0.0482	0.0446	0.0517	0.0809	0.0453
% RSD	4.31	6.14	1.42	3.57	4.13	5.49	4.96	2.78	2.70	3.12	4.90	2.78
	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t
CDN-HC2-1	14.7	15	15	16	15.0	< 50	16.5	15.6	15.0	13.2	15	14.9
CDN-HC2-2	13.6	16	16	15	14.6	< 50	15.9	16.1	15.1	13.3	15	14.6
CDN-HC2-3	15.8	16	15	15	14.1	< 50	15.7	16.2	15.2	13.2	15	14.3
CDN-HC2-4	14.6	14	17	15	14.5	< 50	16.1	15.7	15.1	13.8	15	14.1
CDN-HC2-5	13.8	16	17	15	14.6	< 50	16.3	15.8	15.0	13.0	15	16.7
CDN-HC2-6	14.0	15	17	15	14.1	< 50	16.3	15.9	15.2	13.3	15	14.8
CDN-HC2-7	15.9	15	16	15	14.3	< 50	15.8	15.5	15.2	13.0	15	15.3
CDN-HC2-8	12.4	16	17	15	14.5	< 50	15.6	15.8	15.5	13.3	15	14.9
CDN-HC2-9	16.4	16	18	15	15.3	< 50	16.2	15.4	15.2	13.2	15	14.7
CDN-HC2-10	15.1	16	18	16	15.1	< 50	16.1	15.4	15.1	13.1	15	15.4
Mean	14.6	15.5	16.6	15.2	14.6		16.1	15.7	15.2	13.2	15.0	15.0
Std. Devn.	1.2230	0.7071	1.0750	0.4216	0.4095		0.2915	0.2757	0.1430	0.2184	0.0000	0.7200
% RSD	8.36	4.56	6.48	2.77	2.80		1.82	1.75	0.94	1.65	0.00	4.81

**NOTE: Au data from Lab. 2 was excluded for failing the “t” test.**

**Ag data from Lab. 10 was excluded for failing the “t” test.**

**STANDARD REFERENCE MATERIAL CDN-HC-2**

	Lab 1	Lab 2	Lab 3	Lab 4	Lab 5	Lab 6	Lab 7	Lab 8	Lab 9	Lab 10	Lab 11	Lab 12
	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu
CDN-HC2-1	4.41	4.67	4.61	4.88	4.90	4.40	4.82	4.47	4.61	4.81	4.34	4.54
CDN-HC2-2	4.46	4.72	4.60	4.58	4.62	4.69	4.72	4.45	4.61	4.70	4.51	4.53
CDN-HC2-3	4.45	4.75	4.67	4.62	4.72	5.06	4.87	4.52	4.61	4.80	4.42	4.53
CDN-HC2-4	4.48	4.69	4.71	4.55	4.75	4.77	4.80	4.50	4.60	4.73	4.47	4.58
CDN-HC2-5	4.53	4.68	4.87	4.58	4.58	4.70	4.83	4.54	4.61	4.78	4.31	4.62
CDN-HC2-6	4.39	4.69	4.70	4.54	4.57	4.83	4.60	4.52	4.60	4.76	4.56	4.57
CDN-HC2-7	4.48	4.66	4.70	4.38	4.67	4.88	4.62	4.47	4.60	4.67	4.40	4.57
CDN-HC2-8	4.43	4.72	4.69	4.47	4.73	4.82	4.78	4.53	4.60	4.75	4.46	4.54
CDN-HC2-9	4.50	4.70	4.70	4.55	4.77	4.69	4.77	4.45	4.61	4.72	4.47	4.54
CDN-HC2-10	4.60	4.61	4.75	4.55	4.74	4.81	4.96	4.48	4.60	4.75	4.41	4.64
Mean	4.47	4.69	4.70	4.57	4.71	4.77	4.78	4.49	4.60	4.75	4.44	4.57
Std. Devn.	0.0611	0.0384	0.0733	0.1278	0.0992	0.1694	0.1088	0.0333	0.0056	0.0437	0.0753	0.0376
% RSD	1.37	0.82	1.56	2.80	2.11	3.55	2.28	0.74	0.12	0.92	1.70	0.82
	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb
CDN-HC2-1	0.46	0.461	0.49	0.474	0.517	0.463	0.51	0.46	0.500	0.449	0.450	0.478
CDN-HC2-2	0.45	0.465	0.48	0.480	0.505	0.463	0.50	0.47	0.496	0.447	0.464	0.476
CDN-HC2-3	0.44	0.489	0.50	0.481	0.496	0.487	0.51	0.47	0.498	0.453	0.456	0.484
CDN-HC2-4	0.45	0.480	0.49	0.472	0.500	0.469	0.50	0.47	0.493	0.452	0.476	0.482
CDN-HC2-5	0.44	0.475	0.50	0.475	0.497	0.478	0.48	0.46	0.496	0.447	0.452	0.490
CDN-HC2-6	0.45	0.470	0.50	0.472	0.488	0.473	0.49	0.47	0.501	0.454	0.470	0.492
CDN-HC2-7	0.45	0.479	0.49	0.466	0.492	0.460	0.47	0.47	0.493	0.449	0.458	0.478
CDN-HC2-8	0.47	0.467	0.50	0.464	0.492	0.476	0.50	0.46	0.501	0.447	0.466	0.481
CDN-HC2-9	0.47	0.472	0.51	0.472	0.497	0.467	0.53	0.46	0.495	0.450	0.462	0.481
CDN-HC2-10	0.45	0.470	0.50	0.472	0.495	0.464	0.48	0.47	0.501	0.448	0.464	0.488
Mean	0.453	0.473	0.496	0.473	0.498	0.470	0.497	0.466	0.497	0.450	0.462	0.483
Std. Devn.	0.0106	0.0082	0.0084	0.0053	0.0082	0.0084	0.0177	0.0052	0.0032	0.0026	0.0080	0.0053
% RSD	2.34	1.74	1.70	1.12	1.64	1.80	3.56	1.11	0.65	0.58	1.74	1.10
	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn
CDN-HC2-1	0.25	0.258	0.26	0.253	0.275	0.240	0.27	0.26	0.263	0.255	0.245	0.262
CDN-HC2-2	0.24	0.266	0.25	0.250	0.268	0.251	0.27	0.26	0.264	0.256	0.254	0.262
CDN-HC2-3	0.24	0.268	0.26	0.247	0.264	0.268	0.27	0.26	0.269	0.261	0.246	0.267
CDN-HC2-4	0.24	0.262	0.27	0.247	0.267	0.252	0.26	0.26	0.265	0.262	0.256	0.262
CDN-HC2-5	0.24	0.259	0.25	0.247	0.265	0.256	0.26	0.26	0.263	0.256	0.247	0.260
CDN-HC2-6	0.25	0.258	0.26	0.250	0.259	0.257	0.27	0.26	0.266	0.260	0.252	0.267
CDN-HC2-7	0.25	0.264	0.25	0.240	0.260	0.254	0.27	0.26	0.262	0.258	0.249	0.261
CDN-HC2-8	0.25	0.264	0.26	0.240	0.259	0.257	0.26	0.26	0.268	0.257	0.252	0.260
CDN-HC2-9	0.25	0.273	0.26	0.244	0.262	0.251	0.27	0.26	0.264	0.257	0.250	0.262
CDN-HC2-10	0.25	0.270	0.26	0.245	0.261	0.252	0.26	0.26	0.264	0.258	0.254	0.269
Mean	0.246	0.264	0.258	0.246	0.264	0.254	0.266	0.260	0.265	0.258	0.251	0.263
Std. Devn.	0.0052	0.0051	0.0063	0.0042	0.0050	0.0070	0.0052	0.0000	0.0023	0.0023	0.0037	0.0034
% RSD	2.10	1.94	2.45	1.71	1.90	2.75	1.94	0.00	0.85	0.90	1.48	1.29

**NOTE: Pb data from Lab. 8 was excluded from the data set for failing the “t” test.  
Zn data from Lab.2 was excluded from the data set for failing the “t” test.**

**STANDARD REFERENCE MATERIAL CDN-HC-2**

**Participating Laboratories:**


(not in same order as listed in table of results)

Acme Analytical Laboratories Ltd., Vancouver  
Assayers Canada Ltd., Vancouver  
ALS Chemex Laboratories, North Vancouver  
Actlabs, Ontario, Canada  
Alex Stewart Assayers (Argentina) Ltd.  
Genalysis Laboratory, Australia  
Labtium Laboratory, Finland  
OMAC Laboratory Ltd., Ireland  
Skyline Laboratory, Arizona, USA  
Teck Cominco - Global Discovery Laboratory, Vancouver  
TSL Laboratories Ltd., Saskatoon  
Ultra Trace Analytical Laboratories, Australia


Legal Notice:

This certificate and the reference material described in it have been prepared with due care and attention. However CDN Resource Laboratories Ltd. or Barry Smee accept no liability for any decisions or actions taken following the use of the reference material. Our liability is limited solely to the cost of the reference material.

Certified by

  
Duncan Sanderson, Certified Assayer of B.C.

Geochemist

  
Dr. Barry Smee, Ph.D., P. Geo.