

CDN Resource Laboratories Ltd.

#2, 20148 – 102 Avenue, Langley, B.C., Canada, V1M 4B4, 604-882-8422, Fax: 604-882-8466 (www.cdnlabs.com)

ORE REFERENCE STANDARD: CDN-ME-1

Recommended values and the “Between Lab” Two Standard Deviations

<i>Gold</i>	<i>0.87</i>	\pm	<i>0.09 g/t</i>
<i>Silver</i>	<i>39.3</i>	\pm	<i>4.6 g/t</i>
<i>Copper</i>	<i>0.011</i>	\pm	<i>0.001 %</i>
<i>Lead</i>	<i>0.324</i>	\pm	<i>0.020 %</i>
<i>Zinc</i>	<i>0.347</i>	\pm	<i>0.028 %</i>

PREPARED BY: CDN Resource Laboratories Ltd.
CERTIFIED BY: Duncan Sanderson, B.Sc., Licensed Assayer of British Columbia
INDEPENDENT GEOCHEMIST: Dr. Barry Smee., Ph.D., P. Geo.
DATE OF CERTIFICATION: March 19, 2009

METHOD OF PREPARATION:

Reject ore material was dried, crushed, pulverized and then passed through a 270 mesh screen. The +270 material was discarded. The -270 material was mixed for 6 days in a double-cone mixer. Splits were taken and sent to twelve laboratories for round robin assaying.

ORIGIN OF REFERENCE MATERIAL:

Standard CDN-ME-1 was made using ore supplied by Minera San Xavier from their Cerro de San Pedro deposit in San Luis Potosi, Mexico. The ore is from an oxidized, porphyry system.

Approximate chemical composition is as follows:

	Percent			Percent
SiO ₂	57.0		MgO	0.6
Al ₂ O ₃	16.3		K ₂ O	5.3
Fe ₂ O ₃	10.2		TiO ₂	0.9
CaO	0.7		LOI	6.5
Na ₂ O	0.1		S	0.4

Statistical Procedures:

The final limits were calculated after first determining if all data was compatible within a spread normally expected for similar analytical methods done by reputable laboratories. Data from any one laboratory was removed from further calculations when the mean of all analyses from that laboratory failed a t test of the global means of the other laboratories. The means and standard deviations were calculated using all remaining data. Any analysis that fell outside of the mean ± 2 standard deviations was removed from the ensuing data base. The mean and standard deviations were again calculated using the remaining data. This method is different from that used by Government agencies in that the actual “between-laboratory” standard deviation is used in the calculations. This produces upper and lower limits that reflect actual individual analyses rather than a grouped set of analyses. The limits can therefore be used to monitor accuracy from individual analyses, unlike the Confidence Limits published on other standards.

Assay Procedures:

Au: Fire assay pre-concentration, AA or ICP finish (30g sub-sample).
Ag, Cu, Pb, Zn: 4-acid digestion, AA or ICP finish.

STANDARD REFERENCE MATERIAL CDN-ME-1

Results from round-robin assaying:

	Lab 1	Lab 2	Lab 3	Lab 4	Lab 5	Lab 6	Lab 7	Lab 8	Lab 9	Lab 10	Lab 11	Lab 12
	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t	Au g/t
CDN-ME-1	0.82	0.81	0.89	0.925	0.897	0.919	0.836	0.867	0.83	0.93	0.878	0.85
CDN-ME-2	0.81	0.87	0.87	0.886	0.940	0.955	0.819	0.893	0.91	0.85	0.881	0.89
CDN-ME-3	0.83	0.86	0.89	0.844	0.856	0.974	0.724	0.879	0.85	0.93	0.930	0.87
CDN-ME-4	0.80	0.93	0.83	0.877	0.907	0.875	0.761	0.844	0.84	0.84	0.752	0.88
CDN-ME-5	0.80	0.85	0.79	0.940	0.891	0.901	0.764	0.868	0.84	0.85	0.720	0.89
CDN-ME-6	0.81	0.81	0.83	1.180	0.892	0.861	0.701	0.809	0.82	0.86	0.857	0.94
CDN-ME-7	0.84	0.89	0.80	0.879	0.993	0.942	0.733	0.842	0.98	0.86	0.877	0.90
CDN-ME-8	0.85	0.90	0.82	1.050	0.854	1.040	0.862	0.870	0.86	0.92	0.831	0.92
CDN-ME-9	0.84	0.90	0.81	0.928	0.865	0.844	0.811	0.843	0.86	0.92	0.853	0.83
CDN-ME-10	0.86	0.95	0.85	0.866	0.935	0.926	0.813	0.896	0.85	0.86	0.813	0.92
Mean	0.826	0.877	0.838	0.938	0.903	0.924	0.782	0.861	0.864	0.882	0.839	0.889
Std. Devn.	0.0212	0.0464	0.0358	0.1029	0.0433	0.0583	0.0533	0.0267	0.0474	0.0377	0.0632	0.0335
% RSD	2.57	5.30	4.28	10.98	4.79	6.31	6.81	3.10	5.49	4.27	7.54	3.77
	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t
CDN-ME-1	35.8	38	39	41.3		41	42.9	39	43.0	46.9	42	39.3
CDN-ME-2	36.0	35	39	38.9		38	38.8	37	37.1	39.3	44	39.0
CDN-ME-3	33.6	37	37	37.5		38	39.1	36	32.8	41.9	39	39.5
CDN-ME-4	37.5	35	42	40.6		37	39.7	38	40.0	43.1	42	39.6
CDN-ME-5	33.4	39	40	37.6		37	41.5	39	37.9	42.6	37	37.7
CDN-ME-6	34.6	36	38	42.5		40	42.7	35	42.7	46.2	35	40.3
CDN-ME-7	37.3	37	41	43.6		43	40.6	36	37.4	38.6	41	41.7
CDN-ME-8	34.1	36	41	41.8		39	37.7	37	40.6	39.6	39	39.5
CDN-ME-9	34.6	39	40	45.9		39	43.2	35	41.4	41.9	46	39.6
CDN-ME-10	35.2	40	38	39.3		40	41.3	36	34.7	45.4	40	40.7
Mean	35.2	37.2	39.5	40.9		39.2	40.8	36.8	38.8	42.5	40.5	39.7
Std. Devn.	1.431	1.751	1.581	2.686		1.874	1.893	1.476	3.379	2.917	3.240	1.067
% RSD	4.06	4.71	4.00	6.57		4.78	4.64	4.01	8.72	6.86	8.00	2.69

NOTES:

- 1). Lab 5 was unable to provide 4-acid digestion data for Ag, Cu, Pb, Zn
- 2). Ag data from Lab. 1 was excluded for failing the "t" test.
- 3). Cu data from both Labs 1 and 7 was excluded for failing the "t" test.
- 4). Pb data from Lab 10 was excluded for failing the "t" test.

STANDARD REFERENCE MATERIAL CDN-ME-1

	Lab 1	Lab 2	Lab 3	Lab 4	Lab 5	Lab 6	Lab 7	Lab 8	Lab 9	Lab 10	Lab 11	Lab 12
	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu
CDN-ME-1	0.013	0.011	0.011	0.011		0.01	0.013	0.012	0.011	0.011	0.011	0.011
CDN-ME-2	0.011	0.011	0.011	0.011		0.01	0.013	0.011	0.011	0.011	0.011	0.011
CDN-ME-3	0.011	0.011	0.011	0.011		0.01	0.013	0.011	0.011	0.011	0.011	0.011
CDN-ME-4	0.012	0.011	0.011	0.011		0.01	0.013	0.012	0.011	0.011	0.011	0.011
CDN-ME-5	0.011	0.011	0.010	0.011		0.01	0.013	0.012	0.011	0.012	0.011	0.011
CDN-ME-6	0.013	0.011	0.011	0.011		0.01	0.014	0.011	0.011	0.011	0.011	0.011
CDN-ME-7	0.014	0.012	0.011	0.011		0.01	0.014	0.011	0.011	0.011	0.011	0.011
CDN-ME-8	0.015	0.011	0.011	0.011		0.01	0.014	0.011	0.011	0.012	0.011	0.011
CDN-ME-9	0.013	0.012	0.011	0.011		0.01	0.014	0.011	0.011	0.011	0.011	0.011
CDN-ME-10	0.012	0.012	0.011	0.011		0.01	0.014	0.010	0.011	0.011	0.011	0.011
Mean	0.013	0.011	0.011	0.011		0.010	0.014	0.011	0.011	0.011	0.011	0.011
Std. Devn.	0.0014	0.0001	0.0003	0.0002		0.0003	0.0005	0.0006	0.0001	0.0001	0.0001	0.0001
% RSD	10.83	1.12	2.90	1.52		3.13	3.90	5.65	1.26	1.11	1.26	0.84
	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb	% Pb
CDN-ME-1	0.32	0.326	0.33	0.313		0.340	0.319	0.320	0.302	0.356	0.331	0.318
CDN-ME-2	0.33	0.330	0.33	0.305		0.361	0.323	0.323	0.297	0.340	0.331	0.321
CDN-ME-3	0.32	0.333	0.33	0.309		0.345	0.313	0.323	0.301	0.357	0.338	0.322
CDN-ME-4	0.32	0.331	0.33	0.317		0.330	0.324	0.323	0.303	0.339	0.332	0.324
CDN-ME-5	0.32	0.332	0.31	0.309		0.338	0.307	0.323	0.307	0.361	0.329	0.324
CDN-ME-6	0.32	0.337	0.33	0.311		0.341	0.321	0.323	0.307	0.361	0.328	0.326
CDN-ME-7	0.31	0.331	0.32	0.313		0.344	0.325	0.322	0.308	0.349	0.331	0.326
CDN-ME-8	0.32	0.327	0.33	0.302		0.339	0.330	0.323	0.307	0.356	0.334	0.326
CDN-ME-9	0.33	0.329	0.33	0.321		0.339	0.319	0.323	0.316	0.351	0.335	0.326
CDN-ME-10	0.32	0.329	0.32	0.315		0.342	0.327	0.324	0.303	0.353	0.334	0.326
Mean	0.321	0.330	0.326	0.312		0.342	0.321	0.323	0.305	0.352	0.332	0.324
Std. Devn.	0.0057	0.0030	0.0070	0.0056		0.0079	0.0068	0.0011	0.0052	0.0078	0.0030	0.0029
% RSD	1.77	0.91	2.14	1.80		2.30	2.11	0.33	1.69	2.21	0.90	0.88
	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn
CDN-ME-1	0.33	0.341	0.35	0.337		0.371	0.357	0.328	0.324	0.370	0.351	0.339
CDN-ME-2	0.33	0.343	0.35	0.324		0.392	0.362	0.335	0.326	0.356	0.350	0.341
CDN-ME-3	0.33	0.349	0.36	0.336		0.375	0.356	0.335	0.330	0.370	0.357	0.341
CDN-ME-4	0.33	0.354	0.35	0.340		0.360	0.350	0.340	0.325	0.355	0.349	0.344
CDN-ME-5	0.33	0.357	0.34	0.331		0.370	0.356	0.356	0.336	0.372	0.349	0.343
CDN-ME-6	0.34	0.348	0.35	0.337		0.370	0.360	0.336	0.337	0.377	0.350	0.346
CDN-ME-7	0.35	0.349	0.35	0.337		0.375	0.347	0.326	0.341	0.368	0.349	0.342
CDN-ME-8	0.33	0.340	0.35	0.333		0.371	0.354	0.344	0.336	0.372	0.352	0.343
CDN-ME-9	0.33	0.349	0.35	0.341		0.368	0.358	0.335	0.337	0.362	0.351	0.344
CDN-ME-10	0.33	0.347	0.35	0.341		0.374	0.357	0.326	0.334	0.367	0.351	0.343
Mean	0.333	0.348	0.350	0.336		0.373	0.356	0.336	0.333	0.367	0.351	0.342
Std. Devn.	0.0067	0.0055	0.0047	0.0052		0.0081	0.0044	0.0091	0.0059	0.0070	0.0024	0.0020
% RSD	2.03	1.59	1.35	1.56		2.17	1.25	2.71	1.78	1.92	0.68	0.58

STANDARD REFERENCE MATERIAL CDN-ME-1

Participating Laboratories:


(not in same order as listed in table of results)

Acme Analytical Laboratories Ltd., Vancouver
Assayers Canada Ltd., Vancouver
ALS Chemex Laboratories, North Vancouver
ALS Brisbane Laboratories, Australia
Actlabs, Ontario, Canada
Alex Stewart Assayers (Argentina) Ltd.
Genalysis Laboratory, Australia
Labtium Laboratory, Finland
OMAC Laboratory Ltd., Ireland
Skyline Laboratory, Arizona, USA
TSL Laboratories Ltd., Saskatoon
Ultra Trace Analytical Laboratories, Australia


Legal Notice:

This certificate and the reference material described in it have been prepared with due care and attention. However CDN Resource Laboratories Ltd. or Barry Smee accept no liability for any decisions or actions taken following the use of the reference material. Our liability is limited solely to the cost of the reference material.

Certified by


Duncan Sanderson, Certified Assayer of B.C.

Geochemist


Dr. Barry Smee, Ph.D., P. Geo.