

CDN Resource Laboratories Ltd.

#2, 20148 – 102nd Ave, Langley, B.C., Canada, V1M 4B4, 604-882-8422, Fax: 604-882-8466 (www.cdnlabs.com)

REFERENCE MATERIAL: CDN-ME-1209

Recommended values and the “Between Lab” Two Standard Deviations

<i>Silver</i>	<i>37.1 g/t ± 3.2 g/t</i>	<i>Certified value</i>
<i>Copper</i>	<i>0.370 % ± 0.034 %</i>	<i>Certified value</i>
<i>Zinc</i>	<i>0.224 % ± 0.018 %</i>	<i>Certified value</i>

Note: Standards with an RSD of near or less than 5% are certified; RSD's of between 5% and 15% are Provisional; RSD's over 15% are Indicated. Provisional and Indicated values cannot be used to monitor accuracy with a high degree of certainty.

PREPARED BY: CDN Resource Laboratories Ltd.
CERTIFIED BY: Duncan Sanderson, B.Sc., Licensed Assayer of British Columbia
INDEPENDENT GEOCHEMIST: Dr. Barry Smee., Ph.D., P. Geo.
DATE OF CERTIFICATION: January 10, 2013

METHOD OF PREPARATION:

Reject ore material was dried, crushed, pulverized and then passed through a 270 mesh screen. The +270 material was discarded. The -270 material was mixed for 5 days in a double-cone mixer. Splits were taken and sent to 15 laboratories for round robin assaying.

ORIGIN OF REFERENCE MATERIAL:

The material for CDN-ME-1209 was supplied by Amarc Resources Ltd. from their Silver Vista property. It is described as an immature, fossiliferous sand- and siltstone from central British Columbia hosting fine disseminated Ag-Cu mineralization. The primary ore mineralogy includes native silver, argentite/acanthite, argentiferous chalcocite & digenite, Ag-tennantite, chalcocite, digenite/bornite, chalcopyrite and covellite.

Approximate chemical composition (from whole rock analysis) is as follows:

	Percent		Percent
SiO ₂	67.2	MgO	0.6
Al ₂ O ₃	11.7	K ₂ O	0.2
Fe ₂ O ₃	6.2	TiO ₂	0.6
CaO	3.0	LOI	9.3
Na ₂ O	<0.1	S	0.1
C	1.0		

Statistical Procedures:

The final limits were calculated after first determining if all data was compatible within a spread normally expected for similar analytical methods done by reputable laboratories. Data from any one laboratory was removed from further calculations when the mean of all analyses from that laboratory failed a t test of the global means of the other laboratories. The means and standard deviations were calculated using all remaining data. Any analysis that fell outside of the mean ±2 standard deviations was removed from the ensuing data base. The mean and standard deviations were again calculated using the remaining data. This method is different from that used by Government agencies in that the actual “between-laboratory” standard deviation is used in the calculations. This produces upper and lower limits that reflect actual individual analyses rather than a grouped set of analyses. The limits can therefore be used to monitor accuracy from individual analyses, unlike the Confidence Limits published on other standards.

Assay Procedures:

Au: Fire assay pre-concentration, AA or ICP finish (30g sub-sample).
Ag, Cu, Pb, Zn: 4-acid digestion, AA or ICP finish.

REFERENCE MATERIAL CDN-ME-1209

Results from round-robin assaying:

	Lab 1	Lab 2	Lab 3	Lab 4	Lab 5	Lab 6	Lab 7	Lab 8	Lab 9	Lab 10	Lab 11	Lab 12	Lab 13	Lab 14	Lab 15
	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t	Ag g/t
ME-1209-1	40.2	37.9	39.7	40.2	36	37.8	37.6	41.9	36.9	36.7	35.1	34.4	36.8	37.7	37.0
ME-1209-2	40.0	37.5	39.6	39.9	36	37.9	36.0	39.2	36.7	36.7	33.8	34.3	35.9	37.4	37.3
ME-1209-3	40.0	37.3	36.9	40.5	36	37.3	36.1	38.6	36.5	36.2	34.4	35.0	35.1	36.5	37.2
ME-1209-4	41.5	37.0	37.9	40.6	35	37.1	35.9	38.4	36.5	36.4	34.6	33.8	36.1	36.6	37.1
ME-1209-5	40.8	37.5	38.5	39.6	35	38.2	36.9	39.0	37.0	36.2	34.8	34.9	35.7	36.4	37.9
ME-1209-6	40.6	37.7	39.1	40.8	36	38.1	36.3	39.3	36.5	37.6	35.0	34.4	35.3	36.6	36.3
ME-1209-7	40.3	36.4	37.4	38.8	35	37.9	36.4	37.3	37.3	36.8	35.7	33.8	36.0	37.6	35.6
ME-1209-8	37.4	37.3	37.3	39.9	36	38.0	36.8	40.4	35.9	36.3	36.1	34.3	35.7	37.4	36.8
ME-1209-9	36.7	37.5	37.9	40.1	38	37.3	36.4	40.1	37.1	36.5	35.8	34.7	35.6	37.0	36.4
ME-1209-10	37.4	37.5	38.0	40.6	38	38.2	36.7	39.1	36.6	36.9	36.4	35.1	34.6	37.3	37.3
Mean	39.5	37.4	38.2	40.1	36.1	37.8	36.5	39.3	36.7	36.6	35.2	34.5	35.7	37.1	36.9
Std. Devn.	1.6730	0.4142	0.9696	0.5944	1.1005	0.4022	0.5087	1.2490	0.3972	0.4105	0.8179	0.4572	0.5996	0.4905	0.6471
% RSD	4.24	1.11	2.54	1.48	3.05	1.06	1.39	3.18	1.08	1.12	2.33	1.33	1.68	1.32	1.75
	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu	% Cu
ME-1209-1	0.372	0.385	0.386	0.406	0.371	0.361	0.345	0.398	0.35	0.367	0.348	0.374	0.379	0.391	0.395
ME-1209-2	0.376	0.378	0.391	0.407	0.369	0.364	0.334	0.370	0.35	0.367	0.346	0.379	0.380	0.398	0.393
ME-1209-3	0.374	0.375	0.360	0.415	0.365	0.358	0.335	0.364	0.35	0.359	0.343	0.371	0.380	0.392	0.393
ME-1209-4	0.390	0.374	0.385	0.415	0.368	0.362	0.332	0.369	0.35	0.357	0.339	0.378	0.384	0.393	0.396
ME-1209-5	0.389	0.370	0.372	0.401	0.363	0.362	0.332	0.378	0.35	0.374	0.344	0.376	0.379	0.395	0.395
ME-1209-6	0.380	0.380	0.385	0.421	0.370	0.364	0.338	0.387	0.34	0.355	0.344	0.383	0.380	0.391	0.390
ME-1209-7	0.379	0.364	0.371	0.391	0.366	0.361	0.337	0.375	0.34	0.361	0.339	0.376	0.376	0.397	0.388
ME-1209-8	0.346	0.373	0.368	0.395	0.366	0.359	0.339	0.394	0.35	0.366	0.342	0.378	0.384	0.393	0.388
ME-1209-9	0.362	0.373	0.374	0.412	0.393	0.362	0.338	0.362	0.34	0.362	0.348	0.372	0.379	0.399	0.387
ME-1209-10	0.351	0.366	0.376	0.412	0.380	0.358	0.335	0.395	0.35	0.364	0.346	0.378	0.375	0.394	0.388
Mean	0.372	0.374	0.377	0.408	0.371	0.361	0.337	0.379	0.347	0.363	0.344	0.377	0.380	0.394	0.391
Std. Devn.	0.0148	0.0064	0.0097	0.0095	0.0090	0.0024	0.0039	0.0134	0.0048	0.0056	0.0032	0.0035	0.0029	0.0027	0.0035
% RSD	3.97	1.70	2.57	2.33	2.43	0.66	1.15	3.54	1.39	1.54	0.94	0.94	0.76	0.69	0.89
	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn	% Zn
ME-1209-1	0.23	0.234	0.231	0.226	0.228	0.227	0.231	0.221	0.24	0.221	0.210	0.204	0.229	0.231	0.230
ME-1209-2	0.23	0.233	0.230	0.227	0.228	0.229	0.228	0.211	0.24	0.225	0.204	0.209	0.227	0.225	0.231
ME-1209-3	0.23	0.234	0.216	0.231	0.222	0.220	0.229	0.200	0.24	0.222	0.207	0.208	0.225	0.220	0.233
ME-1209-4	0.24	0.231	0.224	0.227	0.227	0.222	0.230	0.206	0.24	0.216	0.206	0.205	0.229	0.220	0.232
ME-1209-5	0.23	0.234	0.224	0.225	0.223	0.222	0.225	0.207	0.24	0.229	0.206	0.207	0.228	0.219	0.230
ME-1209-6	0.23	0.234	0.228	0.234	0.228	0.226	0.225	0.213	0.24	0.224	0.211	0.203	0.227	0.222	0.230
ME-1209-7	0.23	0.224	0.224	0.220	0.224	0.224	0.228	0.196	0.24	0.223	0.205	0.211	0.224	0.223	0.230
ME-1209-8	0.21	0.232	0.222	0.224	0.226	0.220	0.230	0.209	0.24	0.226	0.209	0.208	0.228	0.222	0.231
ME-1209-9	0.22	0.231	0.226	0.229	0.243	0.222	0.230	0.198	0.24	0.221	0.209	0.211	0.228	0.223	0.228
ME-1209-10	0.21	0.233	0.222	0.226	0.229	0.220	0.229	0.205	0.24	0.224	0.209	0.217	0.224	0.220	0.228
Mean	0.226	0.232	0.225	0.227	0.228	0.223	0.228	0.207	0.240	0.223	0.208	0.208	0.227	0.222	0.230
Std. Devn.	0.0097	0.0030	0.0044	0.0038	0.0058	0.0031	0.0020	0.0075	0.0000	0.0035	0.0023	0.0041	0.0020	0.0033	0.0016
% RSD	4.27	1.30	1.95	1.69	2.57	1.39	0.87	3.63	0.00	1.56	1.12	1.96	0.90	1.51	0.68

Note: Cu data from Lab 4 was removed for failing the t test.

REFERENCE MATERIAL CDN-ME-1209

Participating Laboratories:


(not in same order as listed in table of results)

Acme Analytical Laboratories Ltd., Vancouver, B.C., Canada
Acme Analytical Laboratories Ltd., Santiago, Chile
Actlabs, Ancaster, Ontario, Canada
Actlabs, Thunder Bay, Ontario, Canada
AGAT, Mississauga, Ontario, Canada
ALS Chemex Laboratories, North Vancouver, B.C., Canada
Alex Stewart Argentina SA
CIMM, Lima, Peru
Genalysis, Perth, Australia
Inspectorate Exploration & Mining Services, Richmond, B.C., Canada
SGS, Lima, Peru
SGS, Toronto, Ontario, Canada
SGS, Vancouver, B.C., Canada
TSL Laboratories, Saskatoon, Canada
Ultra Trace, Perth, Australia


Legal Notice:

This certificate and the reference material described in it have been prepared with due care and attention. However CDN Resource Laboratories Ltd. or Barry Smee accept no liability for any decisions or actions taken following the use of the reference material. Our liability is limited solely to the cost of the reference material.

Certified by


Duncan Sanderson, Certified Assayer of B.C.

Geochemist


Dr. Barry Smee, Ph.D., P. Geo.