

CDN Resource Laboratories Ltd.

#2, 20148 – 102nd Ave, Langley, B.C., Canada, V1M 4B4, 604-882-8422, Fax: 604-882-8466 (www.cdnlabs.com)

REFERENCE MATERIAL: CDN-ME-1408

Recommended values and the “Between Lab” Two Standard Deviations

<i>Gold</i>	<i>2.94 g/t ± 0.21 g/t</i>	<i>Certified value</i>
<i>Silver (FA)</i>	<i>396 g/t ± 13 g/t</i>	<i>Certified value</i>
<i>Copper</i>	<i>0.285 % ± 0.012 %</i>	<i>Certified value</i>
<i>Lead</i>	<i>6.53 % ± 0.31 %</i>	<i>Certified value</i>
<i>Zinc</i>	<i>0.851 % ± 0.040 %</i>	<i>Certified value</i>

Note: Standards with an RSD of near or less than 5% are certified; RSD's of between 5% and 15% are Provisional; RSD's over 15% are Indicated. Provisional and Indicated values cannot be used to monitor accuracy with a high degree of certainty.

PREPARED BY: CDN Resource Laboratories Ltd.
CERTIFIED BY: Duncan Sanderson, B.Sc., Licensed Assayer of British Columbia
INDEPENDENT GEOCHEMIST: Dr. Barry Smee., Ph.D., P. Geo.
DATE OF CERTIFICATION: November 3, 2014

METHOD OF PREPARATION:

Reject ore material was dried, crushed, pulverized and then passed through a 270 mesh screen. The +270 material was discarded. The -270 material was mixed for 5 days in a double-cone mixer. Splits were taken and sent to 15 laboratories for round robin assaying.

ORIGIN OF REFERENCE MATERIAL:

Standard CDN-ME-1408 was made using a variety of different ores.

Approximate chemical composition (from whole rock analysis) is as follows:

	Percent		Percent
SiO ₂	53.7	MgO	1.8
Al ₂ O ₃	13.4	K ₂ O	1.9
Fe ₂ O ₃	8.9	TiO ₂	0.4
CaO	3.8	LOI	4.5
Na ₂ O	2.1	S	2.5
C	0.6		

Statistical Procedures:

The final limits were calculated after first determining if all data was compatible within a spread normally expected for similar analytical methods done by reputable laboratories. Data from any one laboratory was removed from further calculations when the mean of all analyses from that laboratory failed a t test of the global means of the other laboratories. The means and standard deviations were calculated using all remaining data. Any analysis that fell outside of the mean ± 2 standard deviations was removed from the ensuing data base. The mean and standard deviations were again calculated using the remaining data. This method is different from that used by Government agencies in that the actual “between-laboratory” standard deviation is used in the calculations. This produces upper and lower limits that reflect actual individual analyses rather than a grouped set of analyses. The limits can therefore be used to monitor accuracy from individual analyses, unlike the Confidence Limits published on other standards.

Assay Procedures:

Au: Fire assay pre-concentration, AA or ICP finish.
Ag: Fire assay pre-concentration, gravimetric finish.
Cu, Pb, Zn: 4-acid digestion, AA or ICP finish.

REFERENCE MATERIAL CDN-ME-1408

Results from round-robin assaying:

	Lab 1	Lab 2	Lab 3	Lab 4	Lab 5	Lab 6	Lab 7	Lab 8	Lab 9	Lab 10	Lab 11	Lab 12	Lab 13	Lab 14	Lab 15
	Au g/t														
ME-1408-1	2.78	3.15	3.00	2.92	2.94	2.90	2.97	2.93	2.89	2.96	2.90	2.67	2.98	2.79	2.95
ME-1408-2	2.86	3.18	3.18	2.91	2.96	2.83	3.02	2.85	2.82	2.87	3.00	2.66	3.03	2.90	2.97
ME-1408-3	3.06	3.26	3.23	2.93	3.00	2.94	2.93	3.08	2.61	2.84	2.90	2.63	2.82	2.87	2.88
ME-1408-4	2.90	3.12	3.12	3.14	2.97	2.99	2.97	2.92	2.76	2.82	2.91	2.76	2.95	2.79	2.87
ME-1408-5	3.03	2.95	3.31	3.17	3.13	2.97	3.00	3.00	3.06	2.88	2.96	2.90	2.78	2.76	2.90
ME-1408-6	3.14	3.12	3.07	2.89	2.96	2.82	2.94	3.03	3.13	2.95	2.98	2.76	3.10	2.88	2.95
ME-1408-7	2.88	3.09	3.06	3.20	2.92	2.99	2.98	2.96	2.82	2.90	2.92	2.79	2.85	2.82	2.94
ME-1408-8	2.76	3.03	3.11	3.12	3.16	2.92	2.92	3.06	2.90	2.82	3.01	2.78	2.88	2.83	2.89
ME-1408-9	2.76	2.93	2.96	2.89	2.89	2.92	3.03	2.96	2.65	2.91	2.98	2.86	2.76	2.83	2.91
ME-1408-10	2.83	2.83	3.03	3.08	2.93	2.83	2.94	2.98	2.92	2.91	3.01	2.75	2.79	2.72	2.92
Mean	2.90	3.06	3.11	3.03	2.99	2.91	2.97	2.98	2.86	2.89	2.96	2.76	2.89	2.82	2.92
Std. Devn.	0.1336	0.1317	0.1077	0.1276	0.0892	0.0656	0.0400	0.0691	0.1628	0.0495	0.0446	0.0855	0.1170	0.0553	0.0336
% RSD	4.61	4.30	3.47	4.22	2.99	2.25	1.35	2.32	5.70	1.71	1.51	3.10	4.04	1.96	1.15
	Ag g/t														
ME-1408-1	408	386	436	402	402	399	395	388	397	399	409	385	385	382	438
ME-1408-2	399	391	426	397	412	397	394	387	399	391	400	395	383	397	363
ME-1408-3	408	378	434	396	386	399	397	389	411	391	402	389	371	391	397
ME-1408-4	400	399	433	395	373	402	398	390	383	397	399	394	379	393	404
ME-1408-5	401	391	427	395	395	401	402	388	395	401	397	396	381	394	395
ME-1408-6	399	392	434	398	389	398	398	392	393	392	395	407	378	394	394
ME-1408-7	410	393	433	407	399	401	396	390	403	393	404	387	377	388	405
ME-1408-8	402	402	427	403	371	400	398	391	405	395	400	395	387	388	399
ME-1408-9	405	395	456	400	375	397	398	389	395	391	396	407	388	389	398
ME-1408-10	397	396	413	407	369	398	396	388	383	392	398	402	385	395	401
Mean	403	392	432	400	387	399	397	389	396	394	400	396	381	391	399
Std. Devn.	4.53	6.73	10.80	4.59	14.84	1.75	2.20	1.55	8.90	3.65	4.13	7.67	5.25	4.45	18.03
% RSD	1.12	1.72	2.50	1.15	3.83	0.44	0.55	0.40	2.24	0.92	1.03	1.94	1.38	1.14	4.51

Notes: Ag data from laboratory 3 was removed for failing the t test.

REFERENCE MATERIAL *CDN-ME-1408*

Results from round-robin assaying:

	Lab 1	Lab 2	Lab 3	Lab 4	Lab 5	Lab 6	Lab 7	Lab 8	Lab 9	Lab 10	Lab 11	Lab 12	Lab 13	Lab 14	Lab 15
	% Cu														
ME-1408-1	0.296	0.292	0.286	0.274	0.286	0.294	0.28	0.279	0.310	0.285	0.291	0.292	0.300	0.275	0.279
ME-1408-2	0.283	0.285	0.282	0.280	0.289	0.299	0.29	0.280	0.304	0.282	0.289	0.295	0.310	0.272	0.287
ME-1408-3	0.294	0.291	0.283	0.278	0.291	0.283	0.28	0.281	0.308	0.287	0.293	0.298	0.320	0.273	0.286
ME-1408-4	0.277	0.295	0.290	0.282	0.293	0.287	0.29	0.286	0.309	0.283	0.290	0.291	0.310	0.276	0.275
ME-1408-5	0.281	0.290	0.286	0.279	0.289	0.279	0.29	0.278	0.312	0.286	0.292	0.281	0.310	0.278	0.285
ME-1408-6	0.284	0.286	0.289	0.285	0.281	0.285	0.29	0.280	0.308	0.274	0.293	0.294	0.300	0.278	0.282
ME-1408-7	0.284	0.287	0.279	0.274	0.291	0.286	0.29	0.282	0.305	0.282	0.288	0.287	0.310	0.277	0.282
ME-1408-8	0.278	0.281	0.280	0.281	0.293	0.284	0.28	0.278	0.305	0.282	0.290	0.292	0.310	0.276	0.292
ME-1408-9	0.292	0.288	0.276	0.278	0.291	0.289	0.28	0.280	0.302	0.278	0.292	0.296	0.300	0.279	0.287
ME-1408-10	0.280	0.289	0.278	0.273	0.289	0.293	0.28	0.285	0.296	0.292	0.291	0.280	0.300	0.279	0.287
Mean	0.285	0.288	0.283	0.278	0.289	0.288	0.285	0.281	0.306	0.283	0.291	0.291	0.307	0.276	0.284
Std. Devn.	0.0067	0.0039	0.0047	0.0039	0.0036	0.0059	0.0053	0.0027	0.0047	0.0049	0.0017	0.0061	0.0067	0.0022	0.0048
% RSD	2.35	1.37	1.68	1.39	1.24	2.05	1.85	0.97	1.54	1.74	0.57	2.10	2.20	0.80	1.70
	% Pb														
ME-1408-1	6.53	6.65	7.08	6.44	6.76	6.43	6.74	6.38	6.74	6.46	6.53	6.82	6.54	6.42	7.060
ME-1408-2	6.52	6.40	6.99	6.70	6.79	6.54	6.77	6.37	6.61	6.30	6.46	6.74	6.66	6.41	5.890
ME-1408-3	6.58	6.68	6.93	6.27	6.72	6.33	6.75	6.52	6.82	6.36	6.51	6.52	7.03	6.41	6.250
ME-1408-4	6.62	6.76	7.03	6.45	6.87	6.37	6.74	6.46	6.50	6.41	6.51	6.71	6.76	6.45	6.420
ME-1408-5	6.48	6.52	6.87	6.33	6.76	6.34	6.75	6.37	6.59	6.51	6.54	6.35	6.72	6.50	6.420
ME-1408-6	6.67	6.61	6.93	6.58	6.64	6.35	6.72	6.32	6.62	6.31	6.52	6.62	6.56	6.43	6.350
ME-1408-7	6.69	6.61	6.85	6.38	6.88	6.36	6.76	6.31	6.56	6.35	6.51	6.56	6.72	6.46	6.300
ME-1408-8	6.47	6.46	6.80	6.34	6.80	6.39	6.77	6.35	6.56	6.39	6.46	6.44	6.62	6.46	6.370
ME-1408-9	6.64	6.60	6.67	6.65	6.80	6.37	6.78	6.32	6.43	6.31	6.47	6.70	6.61	6.49	6.400
ME-1408-10	6.63	6.47	6.71	6.38	6.85	6.49	6.79	6.31	6.34	6.36	6.53	6.55	6.53	6.51	6.320
Mean	6.58	6.58	6.89	6.45	6.79	6.40	6.76	6.37	6.58	6.38	6.50	6.60	6.68	6.45	6.38
Std. Devn.	0.0776	0.1115	0.1332	0.1446	0.0726	0.0701	0.0211	0.0694	0.1391	0.0683	0.0296	0.1449	0.1480	0.0381	0.2856
% RSD	1.18	1.70	1.93	2.24	1.07	1.10	0.31	1.09	2.12	1.07	0.46	2.20	2.22	0.59	4.48
	% Zn														
ME-1408-1	0.872	0.860	0.838	0.834	0.838	0.887	0.840	0.869	0.901	0.814	0.848	0.890	0.850	0.856	0.810
ME-1408-2	0.851	0.860	0.831	0.855	0.855	0.896	0.850	0.865	0.891	0.826	0.869	0.880	0.860	0.850	0.813
ME-1408-3	0.869	0.860	0.827	0.844	0.852	0.851	0.840	0.868	0.890	0.830	0.856	0.850	0.910	0.853	0.824
ME-1408-4	0.844	0.880	0.842	0.854	0.866	0.861	0.850	0.882	0.894	0.819	0.861	0.870	0.870	0.853	0.808
ME-1408-5	0.856	0.870	0.818	0.851	0.838	0.846	0.850	0.863	0.894	0.832	0.858	0.830	0.860	0.859	0.827
ME-1408-6	0.868	0.860	0.830	0.858	0.814	0.857	0.850	0.865	0.891	0.799	0.845	0.870	0.850	0.852	0.812
ME-1408-7	0.865	0.870	0.815	0.845	0.862	0.857	0.860	0.869	0.873	0.821	0.846	0.850	0.870	0.854	0.812
ME-1408-8	0.851	0.850	0.810	0.852	0.861	0.855	0.850	0.860	0.876	0.824	0.849	0.840	0.860	0.853	0.825
ME-1408-9	0.868	0.860	0.795	0.852	0.840	0.870	0.850	0.864	0.870	0.809	0.853	0.880	0.850	0.858	0.811
ME-1408-10	0.832	0.870	0.805	0.835	0.836	0.877	0.850	0.848	0.853	0.839	0.862	0.860	0.840	0.861	0.824
Mean	0.858	0.864	0.821	0.848	0.846	0.866	0.849	0.865	0.883	0.821	0.855	0.862	0.862	0.855	0.817
Std. Devn.	0.0133	0.0084	0.0151	0.0083	0.0159	0.0164	0.0057	0.0085	0.0147	0.0117	0.0079	0.0193	0.0193	0.0036	0.0074
% RSD	1.55	0.98	1.84	0.98	1.88	1.89	0.67	0.98	1.67	1.43	0.92	2.24	2.24	0.42	0.91

Notes: Cu data from laboratories 9 and 13 was removed for failing the t test.
Pb data from laboratory 3 was removed for failing the t test.

REFERENCE MATERIAL CDN-ME-1408

Participating Laboratories:


(not in same order as listed in table of results)

Bureau Veritas, Vancouver, BC, Canada
Actlabs, Ancaster, Ontario, Canada
Actlabs, Thunder Bay, Ontario, Canada
AGAT, Mississauga, Ontario, Canada
ALS Canada Inc., North Vancouver, BC, Canada
ALS, Loughrea, Ireland (Omac)
American Assay Laboratories, Nevada, USA
Certimin, Lima, Peru
Genalysis, Perth, Australia
Met-Solve, Langley, B.C., Canada
SGS, Lima, Peru
SGS Canada Inc., Burnaby, BC, Canada
Skyline Assayers and Laboratories, Arizona, USA
TSL Laboratories Ltd., Saskatoon, Saskatchewan, Canada
Bureau Veritas, Perth, Australia

Legal Notice:

This certificate and the reference material described in it have been prepared with due care and attention. However CDN Resource Laboratories Ltd. or Barry Smee accept no liability for any decisions or actions taken following the use of the reference material. Our liability is limited solely to the cost of the reference material.

Certified by



Duncan Sanderson, Certified Assayer of B.C.

Geochemist



Dr. Barry Smee, Ph.D., P. Geo.